

MINFILE Number: 082GNW057	Name: JOLLY-MOLLY	Status: Showing
----------------------------------	--------------------------	------------------------

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
VEIN		Copper	1.31 %	a sample (no. 710M) from a massive pyrrhotite-chalcocopyrite vein Property File - Esperanza Explorations Ltd. [1980-03-01]: Property Examination Report - The Mt. Haley Prospect
1979	Assay/analysis Rock	Molybdenum	0.06 %	
DUMP		Copper	0.131 %	a dump sample of monzonite hosting disseminated mineralization Property File - Esperanza Explorations Ltd. [1980-03-01]: Property Examination Report - The Mt. Haley Prospect
	Assay/analysis	Molybdenum	0.015 %	
1979	Grab	Tungsten	0.01 %	
OUTCROP		Zinc	0.658 %	a grab sample (B-439) of outcrop assayed 0.658 per cent zinc, while other talus samples (B-433 to 448) yielded up to 23.65 per cent zinc and 0.11 per cent copper Property File - Aquitaine Co. of Canada Ltd. [1976-02-02]: Report on Southeastern British Columbia Project 1975 for Aquitaine Company of Canada
1975	Assay/analysis Grab			
TRENCH		Copper	1.4 %	chip samples from trench 1 over 55 centimetres from sample H-3 Property File - R. Sheffield [1974-09-06]: Report - Haley #I
	Assay/analysis	Silver	41.0 g/t	
1974	Chip			
TRENCH		Copper	1.05 %	chip samples from trench 1 over 60 centimetres from sample H-1 Property File - R. Sheffield [1974-09-06]: Report - Haley #I). A select dump sample from one of the former adits yielded 95.8 grams per tonne silver (Property File - R. Sheffield [1974-09-06]: Report - Haley #I
	Assay/analysis	Molybdenum	0.014 %	
1974	Chip			
TRENCH		Copper	0.80 %	chip samples from trench 1 over 85 centimetres from sample H-2 Property File - R. Sheffield [1974-09-06]: Report - Haley #I). A select dump sample from one of the former adits yielded 95.8 grams per tonne silver (Property File - R. Sheffield [1974-09-06]: Report - Haley #I
	Assay/analysis	Molybdenum	0.003 %	
1974	Chip			
TRENCH		Copper	1.50 %	chip samples from trench 1 over 95 centimetres from sample H-7 Property File - R. Sheffield [1974-09-06]: Report - Haley #I). A select dump sample from one of the former adits yielded 95.8 grams per tonne silver (Property File - R. Sheffield [1974-09-06]: Report - Haley #I
	Assay/analysis	Molybdenum	0.047 %	
1974	Chip	Silver	4.8 g/t	