MINFILE Number: 082JNW011 **Name:** YELO **Status:** Showing

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
SAMPLE 1976 N	Assay/analysis Grab	Magnesite	41.8000 %	Highest assay was 87.5 per cent MgO (calcined) with 50.2 per cent loss on ignition. Typical assays are 42 to 68 per cent (calcined) MgO. Assessment Report 6565.