

| | | | | | |
|------------------------|-----------|--------------|--------------|----------------|----------|
| MINFILE Number: | 082KNW039 | Name: | SILVER CHIEF | Status: | Prospect |
|------------------------|-----------|--------------|--------------|----------------|----------|

| Ore Zone/ Year/Report On | | Tonnage/ Category | Commodity | Grade | Reference/ Comments |
|-----------------------------|---|------------------------|-----------|-------------|---|
| LOWER | | | Silver | 77.0 g/t | three chip samples (601F through 603F) from the no. 6 (Lower) zone yielded 77.0, 17.1 and 30.8 grams per tonne silver with 19.60, 14.70 and 4.40 per cent lead over 0.45, 2.52 and 2.58 metres, respectively Property File - Tacoma Resources Ltd. [1977-04-28]: Geological Report on the Silver Chief Property |
| 1977 | N | Assay/analysis Chip | Lead | 19.60 % | |
| WEST | | | Silver | 34.2 g/t | Two other chip samples (604F and 605F), taken 225 metres west and 120 metres above the adit, assayed 34.2 and 10.3 grams per tonne silver with 4.95 and 1.45 per cent lead over 1.38 and 1.08 metres, respectively Property File - Tacoma Resources Ltd. [1977-04-28]: Geological Report on the Silver Chief Property |
| 1977 | N | Assay/analysis Chip | Lead | 4.95 % | |
| LOWER | | | Lead | 41.89 % | Property File - A.G. Mackenzie [1971-04-01]: Geological Report on the Silver Chief Claims |
| 1970 | N | Assay/analysis Grab | Silver | 179.9 g/t | |
| NO. 5 | | | Lead | 64.02 % | Property File - A.G. Mackenzie [1971-04-01]: Geological Report on the Silver Chief Claims |
| 1970 | N | Assay/analysis Grab | Silver | 385.8 g/t | |
| NO. 5 | | | Silver | 96.0000 g/t | across 1.0 metre of the no. 5 (Upper) zone Ministry of Energy, Mines and Petroleum Res. Bulletin 45, page 74. |
| 1962 | N | Assay/analysis Chip | Lead | 16.1600 % | |
| NO. 5 | | | Silver | 94.3000 g/t | Sample collected over 1.22 metres. EMPR ASS RPT 360 |
| | | | Gold | 0.5100 g/t | |
| 1960 | N | Assay/analysis Chip | Lead | 16.7000 % | |
| NO. 4 | | | Silver | 167.6 g/t | a sample from the no. 4 zone assayed 167.6 grams per tonne silver and 26.29 per cent lead across 38 centimetres Property File - A.G. Mackenzie [1971-04-01]: Geological Report on the Silver Chief Claims |
| 1960 | N | Assay/analysis Chip | Lead | 26.29 % | |