MINFILE Number: 082KNW039 **Name:** SILVER CHIEF **Status:** Prospect

Ore Zone/ Year/Report On		Tonnage/ Category	Commodity	Grade	Reference/ Comments
LOWER 1977	N	Assay/analysis Chip	Silver Lead	77.0 g/t 19.60 %	three chip samples (601F through 603F) from the no. 6 (Lower) zone yielded 77.0, 17.1 and 30.8 grams per tonne silver with 19.60, 14.70 and 4.40 per cent lead over 0.45, 2.52 and 2.58 metres, respectively Property File - Tacoma Resources Ltd. [1977-04-28]: Geological Report on the Silver Chief Property
WEST 1977	N	Assay/analysis Chip	Silver Lead	34.2 g/t 4.95 %	Two other chip samples (604F and 605F), taken 225 metres west and 120 metres above the adit, assayed 34.2 and 10.3 grams per tonne silver with 4.95 and 1.45 per cent lead over 1.38 and 1.08 metres, respectively Property File - Tacoma Resources Ltd. [1977-04-28]: Geological Report on the Silver Chief Property
LOWER 1970	N	Assay/analysis Grab	Lead Silver	41.89 % 179.9 g/t	Property File - A.G. Mackenzie [1971-04-01]: Geological Report on the Silver Chief Claims
NO. 5 1970	N	Assay/analysis Grab	Lead Silver	64.02 % 385.8 g/t	Property File - A.G. Mackenzie [1971-04-01]: Geological Report on the Silver Chief Claims
NO. 5 1962	N	Assay/analysis Chip	Silver Lead	96.0000 g/t 16.1600 %	across 1.0 metre of the no. 5 (Upper) zone Ministry of Energy, Mines and Petroleum Res. Bulletin 45, page 74.
NO. 5 1960	N	Assay/analysis Chip	Silver Gold Lead	94.3000 g/t 0.5100 g/t 16.7000 %	Sample collected over 1.22 metres. EMPR ASS RPT 360
NO. 4 1960	N	Assay/analysis Chip	Silver Lead	167.6 g/t 26.29 %	a sample from the no. 4 zone assayed 167.6 grams per tonne silver and 26.29 per cent lead across 38 centimetres Property File - A.G. Mackenzie [1971-04-01]: Geological Report on the Silver Chief Claims