

<b>MINFILE Number:</b> 082KNW040	<b>Name:</b> BEATRICE (L.4586)	<b>Status:</b> Past Producer
----------------------------------	--------------------------------	------------------------------

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
ADIT		Lead	17.72 %	A select grab sample (1752214) from the Beatrice upper adit. Chapman, J. (2018-07-15): National Instrument 43-101 Technical Report on the Silver Dollar Property
	Assay/analysis	Zinc	18.91 %	
2017	Grab	Silver	1991 g/t	
OPENCUT		Lead	0.24 %	A composite grab sample (1752204) from a large open cut located above the Beatrice upper adit. Chapman, J. (2018-07-15): National Instrument 43-101 Technical Report on the Silver Dollar Property
	Assay/analysis	Zinc	3.53 %	
2017	Grab	Silver	152 g/t	
		Gold	1.45 g/t	
MAIN	1,360 t	Gold	0.2 g/t	Another 2177 tonnes grading 0.5 gram per tonne gold, 74.9 grams per tonne silver, 0.70 per cent lead and 2.08 per cent zinc. Property File - Dunhill Resources Corp. [1988-01-22]: Geological Report on the Beatrice Property
	Unclassified	Silver	393.0 g/t	
1988		Lead	4.03 %	
		Zinc	7.78 %	
NO. 2		Gold	0.7 g/t	Sampling of the Main vein on the sublevel drift over 0.54 metre. Property File - Dunhill Resources Corp. [1988-01-22]: Geological Report on the Beatrice Property
	Assay/analysis	Silver	1110.5 g/t	
1986	Chip	Lead	11.39 %	
		Zinc	18.2 %	
TOTAL	5,715 t	Silver	465.1 g/t	Property File - R.C. Hart [1982-12-01]: An Analysis of Reports on the Beatrice Property
	Possible	Lead	5.1 %	
1982		Zinc	10.9 %	
NO. 1		Gold	0.7 g/t	A sample from the face of the No.1 adit over 0.84 metre. Property File - R.C. Hart [1982-12-01]: An Analysis of Reports on the Beatrice Property
	Assay/analysis	Silver	485.6 g/t	
1977	Chip	Lead	3.08 %	
		Zinc	12.18 %	
NO. 1		Gold	1.4 g/t	A sample (80327) from the hangingwall of the glory hole zone (Beatrice vein) over 3.6 metres. Property File - Dakota Silver Mines Ltd. [1964-09-08]: Report on the Beatrice Property
	Assay/analysis	Silver	458.3 g/t	
1964	Chip	Lead	2.56 %	
		Zinc	14.99 %	
NO. 2		Gold	0.7 g/t	Sample (80331) from the top of the raise on the No.2 level over 0.96 metre. Property File - Dakota Silver Mines Ltd. [1964-09-08]: Report on the Beatrice Property
	Assay/analysis	Silver	273.6 g/t	
1964	Chip	Lead	3.39 %	
		Zinc	6.51 %	
NO. 2		Gold	2.0 g/t	Sampling of the raise from the No.2 adit over 0.6 metre. Property File - A.E. Wooton [1959-04-01]: A Mineralographic Study of Ore from the Beatrice Mine
	Assay/analysis	Silver	2387 g/t	
1918	Chip	Lead	16.1 %	
		Zinc	31.0 %	
NO. 1		Gold	8.5 g/t	Annual Report 1914, page 267
	Assay/analysis	Silver	4129 g/t	
1914	Rock	Lead	17.42 %	
		Zinc	10 %	

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
NO. 3	Assay/analysis	Gold Silver	5.1 g/t 32.5 g/t	Gold Lode vein Annual Report 1914, page 267
1914	N Rock			