

<b>MINFILE Number:</b>	082KNW059	<b>Name:</b>	ETHEL	<b>Status:</b>	Past Producer
------------------------	-----------	--------------	-------	----------------	---------------

Ore Zone/ Year/Report On		Tonnage/ Category	Commodity	Grade	Reference/ Comments
DUMP			Silver	8164 g/t	dump samples yielded up to 8164 grams per tonne silver, 0.52 per cent lead and 5.52 per cent copper Property File - K.G. Sanders [1975-07-07]: Geological Report on the Ethel Property
		Assay/analysis	Lead	0.52 %	
1975	N	Grab	Copper	5.52 %	
OUTCROP			Gold	0.9 g/t	a chip sample across 0.6 metre of a vein outcrop Property File - K.G. Sanders [1975-07-07]: Geological Report on the Ethel Property
		Assay/analysis	Silver	3528 g/t	
1975	N	Chip			
HIGH-GRADE			Gold	7.5 g/t	a specimen sample of massive freibergite Property File - K.G. Sanders [1975-07-07]: Geological Report on the Ethel Property
		Assay/analysis	Silver	31140 g/t	
1965	N	Rock	Lead	34.85 %	
			Copper	6.60 %	
MAIN		1,633 t	Silver	1197 g/t	The 1965 sampling of the main adit level is reported to have averaged 1197 grams per tonne silver from fifty samples over a 72 centimetre width and a 15 metre vertical distance yielding an indicated or possible ore resource of 1633 tonnes between the surface and the no. 1 level Property File - K.G. Sanders [1975-07-07]: Geological Report on the Ethel Property
		Possible			
1965	N				
UNDERGROUND			Silver	1012 g/t	underground sampling of the levels yielded up to 1012 grams per tonne silver over 0.9 metre from the FW vein on the no. 1 level Property File - K.G. Sanders [1975-07-07]: Geological Report on the Ethel Property
		Assay/analysis			
1965	N	Chip			
UNDERGROUND			Silver	2930 g/t	2930 grams per tonne silver over 1.02 metres from an ore pass between the no. 1 and 2 levels Property File - K.G. Sanders [1975-07-07]: Geological Report on the Ethel Property
		Assay/analysis			
1965	N	Chip			
UNDERGROUND			Silver	1522 g/t	1522 grams per tonne silver and 5.82 per cent lead over 3 metres from the no. 1 vein on a stope between the no. 1A and 2 levels Property File - K.G. Sanders [1975-07-07]: Geological Report on the Ethel Property
		Assay/analysis	Lead	5.82 %	
1965	N	Chip			
UNDERGROUND			Silver	20914 g/t	20914 grams per tonne silver over 0.3 metre from the no. 1 vein on the no. 2 level Property File - K.G. Sanders [1975-07-07]: Geological Report on the Ethel Property
		Assay/analysis			
1965	N	Chip			
UNDERGROUND			Silver	3343 g/t	3343 grams per tonne silver over 0.75 metre from the FW vein on the no. 4 level Property File - K.G. Sanders [1975-07-07]: Geological Report on the Ethel Property
		Assay/analysis			
1965	N	Chip			

Ore Zone/ Year/Report On		Tonnage/ Category	Commodity	Grade	Reference/ Comments
1965	N	Assay/analysis Chip	Silver	4538 g/t	4538 grams per tonne silver over 0.45 metre from the FW vein in the no. 6 level
					Property File - Rexony Mining Co. Ltd. [1965-07-01]: Composite Assay Plan - Ethel Mine
1965	N	Assay/analysis Chip	Silver	823 g/t	the no. 1 vein on the no. 6 level yielded 823 grams per tonne silver over 0.58 metre
					Property File - Rexony Mining Co. Ltd. [1965-07-01]: Composite Assay Plan - Ethel Mine
1964	N	Assay/analysis Chip	Silver	4350 g/t	surface samples of vein outcrops yielded up to 4350
			Lead	7.44 %	grams per tonne silver and 7.44 per cent lead over 45 centimetres
1964	N	Assay/analysis Chip	Silver	153.9 g/t	a sample from the top cross-cut assayed 153.9 grams
			Lead	5.82 %	per tonne silver and 5.82 per cent lead over 30 centimetres
					Property File - K.G. Sanders [1975-07-07]: Geological Report on the Ethel Property