

MINFILE Number:		Name:		Status:	
Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments	
SAMPLE 2011	N	Assay/analysis Grab	Lead Copper Zinc Silver	8.22 % 0.932 % 0.67 % 83.1 g/t	Sample 545571. EMPR ASS RPT 32490
SAMPLE 1996	N	Assay/analysis Chip	Lead Zinc Silver	8.27 % 0.806 % 65.1 g/t	From chip sample 485847 over 0.5 metres. EMPR ASS RPT 24909
SAMPLE 1966	N	Assay/analysis Grab	Silver Lead Zinc	143.9000 g/t 13.0000 % 4.3000 %	Samples of sulphides from trenches A to J in the main showing area across widths that varied from 0.6 to 3.3 metres. Lead assayed from 1.1 to 13 per cent, zinc from trace to 4.3 per cent, and silver from trace to 143.9 grams per tonne. Property File - Sketch map of trenches and drillholes, 1966.