

MINFILE Number:	082LNW031	Name:	FS	Status:	Past Producer
------------------------	-----------	--------------	----	----------------	---------------

Ore Zone/ Year/Report On		Tonnage/ Category	Commodity	Grade	Reference/ Comments
PIT			Silver	758 g/t	grab samples (M-4) across 1.5 metres
2015	N	Assay/analysis Grab	Lead	3.10 %	Assessment Report 36150
PIT			Lead	1.7 %	average of three channel samples (S-2, S-4, S-6) over
1996	N	Assay/analysis Channel	Zinc	0.08 %	3.51 metres
			Silver	377.2 g/t	Assessment Report 25115
PIT			Silver	9.1 g/t	a quartz zone hosting 5 to 15 per cent sulphides over
1996	N	Assay/analysis Drill Core			35.25 metres. A 3.0 metre section, near the end of the
					zone, assayed 9.1 grams per tonne
					Assessment Report 25115
PIT			Lead	1.49 %	In 1981, diamond drilling (hole S-80-5) yielded values
1981	N	Assay/analysis Drill Core	Zinc	1.6 %	up to 520.2 grams per tonne silver, 1.49 per cent lead
			Silver	520.2 g/t	and 1.60 per cent zinc over 1.8 metres; while a 10.2
					metre section averaged 116.3 grams per tonne silver,
					0.164 per cent zinc and 0.156 per cent lead
					Assessment Report 9529
SAMPLE			Silica	46.6000 %	Random sample from northern exposure. Also analysed
1969	N	Assay/analysis Chip			0.064 per cent total Fe, trace Al ₂ O ₃ and nil CaO.
					Open File 1987-15, page 29.