

<b>MINFILE Number:</b> 082LNW031	<b>Name:</b> FS	<b>Status:</b> Past Producer
----------------------------------	-----------------	------------------------------

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
PIT		Silver	758 g/t	grab samples (M-4) across 1.5 metres
	Assay/analysis	Lead	3.10 %	Assessment Report 36150
2015	Grab			
PIT		Lead	1.7 %	average of three channel samples (S-2, S-4, S-6) over
	Assay/analysis	Zinc	0.08 %	3.51 metres
1996	Channel	Silver	377.2 g/t	Assessment Report 25115
PIT		Silver	9.1 g/t	a quartz zone hosting 5 to 15 per cent sulphides over
	Assay/analysis			35.25 metres. A 3.0 metre section, near the end of the
1996	Drill Core			zone, assayed 9.1 grams per tonne
				Assessment Report 25115
PIT		Lead	1.49 %	In 1981, diamond drilling (hole S-80-5) yielded values
	Assay/analysis	Zinc	1.6 %	up to 520.2 grams per tonne silver, 1.49 per cent lead
1981	Drill Core	Silver	520.2 g/t	and 1.60 per cent zinc over 1.8 metres; while a 10.2
				metre section averaged 116.3 grams per tonne silver,
				0.164 per cent zinc and 0.156 per cent lead
				Assessment Report 9529
SAMPLE		Silica	46.6000 %	Random sample from northern exposure. Also analysed
	Assay/analysis			0.064 per cent total Fe, trace Al <sub>2</sub> O <sub>3</sub> and nil CaO.
1969	Chip			Open File 1987-15, page 29.