**MINFILE Number:** 082LSW007 **Name:** BLACK HAWK **Status:** Prospect

| Ore Zone/ Year/Report On | | Tonnage/ Category | Commodity | Grade | Reference/ Comments |
|---|---|---|---|---|---|
| EAST<br>1994 | N | Assay/analysis<br>Channel | Gold<br>Zinc | 5.5 g/t<br>0.12 % | average of a two channel samples over 2.0 metres from the east end of the exposed mineralized zone<br>Assessment Report 23434 |
| EAST<br>1994 | N | Assay/analysis<br>Chip | Gold<br>Zinc | 9.6 g/t<br>0.40 % | average of two chip samples, taken 42 metres north west of the previous samples, over 3.0 metres<br>Assessment Report 23434 |
| WEST<br>1994 | N | Assay/analysis<br>Channel | Gold | 1.2 g/t | a channel sample from the western side of the adit over 1.0 metre<br>Assessment Report 23434 |
| WEST<br>1988 | N | Assay/analysis<br>Grab | Gold | 20.8 g/t | a quartz-ankerite vein in the vicinity of the West showing<br>George Cross Newsletter June 24, 1988 |
| QUARTZ DOME<br>1988 | N | Assay/analysis<br>Chip | Gold | 4.6 g/t | Sampling of a trench exposing the Quartz zone over 2.0 metres<br>George Cross Newsletter June 24, 1988 |
| EAST<br>1986 | N | Assay/analysis<br>Chip | Gold | 8.0 g/t | over 2.1 metres from a short adit near the western end of the East zone<br>Assessment Report 15093 |
| EAST<br>1979 | N | Assay/analysis<br>Drill Core | Gold | 1.7 g/t | over 1.2 metres in hole No. 3<br>Assessment Report 7837 |
| EAST<br>1979 | N | Assay/analysis<br>Drill Core | Gold | 0.5 g/t | over 3.45 metres in hole No. 2<br>Assessment Report 7837 |
| EAST<br>1973 | N | Assay/analysis<br>Chip | Gold | 16.4 g/t | two chip samples yielded 11.3 and 16.4 grams per tonne gold over 3.5 and 4.6 metres, respectively<br>Assessment Report 4797 |
| WEST<br>1973 | N | Assay/analysis<br>Chip | Gold | 16.1 g/t | a chip sample across 1.4 metres of sheared rock in the footwall of the zone<br>Assessment Report 4794 |

| Ore Zone/ Year/Report On | | Tonnage/ Category | Commodity | Grade | Reference/ Comments |
|---|---|---|---|---|---|
| EAST<br><br>1969 | N | Assay/analysis<br>Grab | Gold<br>Silver<br>Zinc<br>Lead | 19.7 g/t<br>13.7 g/t<br>1.85 %<br>0.15 % | average of two samples<br>Assessment Report 2516 |
| WEST<br><br>1922 | N | Assay/analysis<br>Chip | Gold<br>Silver | 10.3 g/t<br>3.4 g/t | over 0.6 metre<br>Assessment Report 4794 |
| EAST<br><br>1919 | N | Assay/analysis<br>Chip | Gold<br>Silver | 19.2 g/t<br>7.8 g/t | surface sampling over 1.8 metres<br>Assessment Report 4797 |