

MINFILE Number: 082LSW015	Name: OCTAGON	Status: Past Producer
----------------------------------	----------------------	------------------------------

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
VEIN 2005	N Assay/analysis Grab	Gold Silver Copper Lead Antimony	28.70 g/t 12893 g/t 3.19 % 3.72 % 1 %	a 5-centimetre sample (T1-15mNHG) of mineralized gouge material Assessment Report 28366
VEIN 2005	N Assay/analysis Chip	Gold Silver Copper Lead Antimony	2.89 g/t 2740 g/t 0.79 % 0.53 % 0.228 %	a 0.7 metre wide sample (T1-15mN) of quartz vein Assessment Report 28366
VEIN 1988	N Assay/analysis Channel	Gold Silver Copper Lead Zinc Antimony	4.90 g/t 941.7 g/t 1.496 % 2.402 % 0.146 % 0.565 %	a 1-metre channel sample (88G15) taken along the strike of a 5.0-centimetre thick sulphide-rich quartz stringer Assessment Report 17664
VEIN 1988	N Assay/analysis Chip	Gold Silver	2.9 g/t 2324.2 g/t	, two chip samples (88DTV-54 and 88DTV-60) of mineralized quartz stringers yielded 2.2 and 2.9 grams per tonne gold with 2204.5 and 2324.2 grams per tonne silver over 0.6 and 0.7 metres, respectively Assessment Report 17928
HIGH-GRADE 1987	N Assay/analysis Grab	Gold Silver	249.7 g/t 102600 g/t	grab samples of select high-grade material from a narrow seam at the hangingwall contact of the quartz vein Assessment Report 16816
MAIN 1985	N Assay/analysis Chip	Gold Silver	7.75 g/t 62.05 g/t	sampling of the main trench over 0.61 metre Assessment Report 28366
MAIN 1985	N Assay/analysis Chip	Gold Silver	0.41 g/t 262.94 g/t	sampling of the main trench over 1.83 metres Assessment Report 28366
VEIN 1985	N Assay/analysis Grab	Gold Silver	2.64 g/t 4456.6 g/t	a sample (495) from 2.5 centimetres of gouge material from the west face of the east open-cut Assessment Report 28366.
VEIN 1985	N Assay/analysis Grab	Gold Silver	250.2 g/t 44943 g/t	select samples of mineralized drusy quartz Assessment Report 28366

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
MAIN 1984	N Assay/analysis Bulk Sample	Silver	14603.4 g/t	a 226.8 kilogram bulk sample from a small pit Property File – Various [1984-03-27]: Notes and Letters Re: Wentorth Tellington Properties
VEIN 1980	N Assay/analysis Rock	Gold Silver Copper	34.9 g/t 44851.9 g/t 5.75 %	Property File – Various [1984-03-27]: Notes and Letters Re: Wentorth Tellington Properties
MAIN 1923	N Assay/analysis Bulk Sample	Silver Gold	1400.0000 g/t 34.0000 g/t	Grades are from a 1.8 tonne bulk sample. Index No. 3, page 207.