MINFILE Number: 082LSW042 **Name:** WHITE ELEPHANT (L. 4880) **Status:** Past Producer

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
DUMP 1988 N	Assay/analysis Grab	Gold Silver	35.6 g/t 27.0 g/t	grab samples from a dump pile Property File - C.J. Sampson [1988-06-30]: Prospectus: Lucky 7 Exploration Ltd., Report on the Geology, Geochemical Soil Sampling, VLF E.M., Magnetometer, Induced Polarization
MAIN 1988 N	Assay/analysis Chip	Gold Silver Bismuth	51.98 g/t 10.9 g/t 0.136 %	a 1.0 metre chip sample (31839) from a quartz body containing a 0.5 metre sulphide bleb Property File - C.J. Sampson [1988-06-30]: Prospectus: Lucky 7 Exploration Ltd., Report on the Geology, Geochemical Soil Sampling, VLF E.M., Magnetometer, Induced Polarization
TRENCH 1980 N	Assay/analysis Grab	Gold Silver	8.6 g/t 17.8 g/t	average of samples from a trench on the upper most mine dump Property File – E.J. Kondra [1980-02-29]: Letters Re: Mineral Claims, Crown Granted Mineral Claims, Vernon Area
UNDERGROUND 1935 N	Assay/analysis Chip	Gold	12.7 g/t	Prior to closing, in 1935, underground development on the 300-foot level is reported to have averaged 12.7 grams per tonne gold over 2.1 metres Property File - C.J. Sampson [1988-06-30]: Prospectus: Lucky 7 Exploration Ltd., Report on the Geology, Geochemical Soil Sampling, VLF E.M., Magnetometer, Induced Polarization