

<b>MINFILE Number:</b> 082LSW042	<b>Name:</b> WHITE ELEPHANT (L. 4880)	<b>Status:</b> Past Producer
----------------------------------	---------------------------------------	------------------------------

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
DUMP		Gold	35.6 g/t	grab samples from a dump pile
1988	N	Silver	27.0 g/t	Property File - C.J. Sampson [1988-06-30]: Prospectus: Lucky 7 Exploration Ltd., Report on the Geology, Geochemical Soil Sampling, VLF E.M., Magnetometer, Induced Polarization
	Assay/analysis Grab			
MAIN		Gold	51.98 g/t	a 1.0 metre chip sample (31839) from a quartz body containing a 0.5 metre sulphide bleb
1988	N	Silver	10.9 g/t	Property File - C.J. Sampson [1988-06-30]: Prospectus: Lucky 7 Exploration Ltd., Report on the Geology, Geochemical Soil Sampling, VLF E.M., Magnetometer, Induced Polarization
	Assay/analysis Chip	Bismuth	0.136 %	
TRENCH		Gold	8.6 g/t	average of samples from a trench on the upper most mine dump
1980	N	Silver	17.8 g/t	Property File – E.J. Kondra [1980-02-29]: Letters Re: Mineral Claims, Crown Granted Mineral Claims, Vernon Area
	Assay/analysis Grab			
UNDERGROUND		Gold	12.7 g/t	Prior to closing, in 1935, underground development on the 300-foot level is reported to have averaged 12.7 grams per tonne gold over 2.1 metres
1935	N			Property File - C.J. Sampson [1988-06-30]: Prospectus: Lucky 7 Exploration Ltd., Report on the Geology, Geochemical Soil Sampling, VLF E.M., Magnetometer, Induced Polarization
	Assay/analysis Chip			