

|                        |           |              |                            |                |         |
|------------------------|-----------|--------------|----------------------------|----------------|---------|
| <b>MINFILE Number:</b> | 082LSW079 | <b>Name:</b> | LITTLE DUNCAN AND PANORAMA | <b>Status:</b> | Showing |
|------------------------|-----------|--------------|----------------------------|----------------|---------|

| Ore Zone/<br>Year/Report On |   | Tonnage/<br>Category   | Commodity | Grade      | Reference/<br>Comments   |
|-----------------------------|---|------------------------|-----------|------------|--|
| SAMPLE<br><br>1988          | N | Assay/analysis<br>Grab | Gold      | 0.14 g/t   | grab sample 88DTJ-72<br>(Assessment Report 17664 and 17928)  |
|                             |   |                        | Silver    | 190.0 g/t  |  |
|                             |   |                        | Lead      | 3.03 %     |  |
|                             |   |                        |           |            |  |
| TRENCH<br><br>1988          | N | Assay/analysis<br>Chip | Gold      | 0.05 g/t   | average of a mix of chip and grab samples over 9.0<br>metres of a trench<br>Assessment Report 17664 and 17928  |
|                             |   |                        | Silver    | 5.6 g/t    |  |
|                             |   |                        |           |            |  |
|                             |   |                        |           |            |  |
| TRENCH<br><br>1983          | N | Assay/analysis<br>Grab | Gold      | 0.3 g/t    | a sample of galena in quartz from a shear zone exposed<br>by trench<br>Assessment Report 12073   |
|                             |   |                        | Silver    | 126.5 g/t  |  |
|                             |   |                        |           |            |  |
|                             |   |                        |           |            |  |
| SAMPLE<br><br>1969          | N | Assay/analysis<br>Chip | Silver    | 123.1 g/t  | two samples, each taken over 1.2 metres, yielded 123.1<br>and 92.3 grams per tonne silver, 2.82 and 3.27 per cent<br>lead with 0.28 and 0.33 per cent zinc, respectively<br>Assessment Report 2552 |
|                             |   |                        | Lead      | 2.82 %     |  |
|                             |   |                        | Zinc      | 0.28 %     |  |
|                             |   |                        |           |            |  |
| HIGH-GRADE<br><br>1968      | N | Assay/analysis<br>Grab | Silver    | 1114.9 g/t | hand picked grab samples yielded from 47.2 to 1114.9<br>grams per tonne silver, 0.17 to 33.20 per cent lead and<br>trace to 34.80 per cent zinc with trace gold<br>Assessment Report 2552          |
|                             |   |                        | Lead      | 33.20 %    |  |
|                             |   |                        | Zinc      | 34.80 %    |  |
|                             |   |                        |           |            |  |