

MINFILE Number:		Name:		Status:	
Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments	
SAMPLE 1988	N	Assay/analysis Grab	Gold Silver Lead	0.14 g/t 190.0 g/t 3.03 %	grab sample 88DTJ-72 (Assessment Report 17664 and 17928)
TRENCH 1988	N	Assay/analysis Chip	Gold Silver	0.05 g/t 5.6 g/t	average of a mix of chip and grab samples over 9.0 metres of a trench Assessment Report 17664 and 17928
TRENCH 1983	N	Assay/analysis Grab	Gold Silver	0.3 g/t 126.5 g/t	a sample of galena in quartz from a shear zone exposed by trench Assessment Report 12073
SAMPLE 1969	N	Assay/analysis Chip	Silver Lead Zinc	123.1 g/t 2.82 % 0.28 %	two samples, each taken over 1.2 metres, yielded 123.1 and 92.3 grams per tonne silver, 2.82 and 3.27 per cent lead with 0.28 and 0.33 per cent zinc, respectively Assessment Report 2552
HIGH-GRADE 1968	N	Assay/analysis Grab	Silver Lead Zinc	1114.9 g/t 33.20 % 34.80 %	hand picked grab samples yielded from 47.2 to 1114.9 grams per tonne silver, 0.17 to 33.20 per cent lead and trace to 34.80 per cent zinc with trace gold Assessment Report 2552