

<b>MINFILE Number:</b> 082LSW111	<b>Name:</b> ZUMAR	<b>Status:</b> Prospect
----------------------------------	--------------------	-------------------------

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
VEIN		Gold	4.22 g/t	
	Assay/analysis	Silver	61.4 g/t	Assessment Report 27711
2004	Rock	Copper	0.256 %	
VEIN		Gold	12.30 g/t	
	Assay/analysis	Silver	180 g/t	Two samples (3816 and 3815) yielded 12.30 and 11.40 grams per tonne gold with 180 and 109 grams per tonne silver over 0.35 and 0.42 metre, respectively.
2001	Chip			Assessment Report 26858
VEIN		Gold	6.38 g/t	
	Assay/analysis	Silver	42.17 g/t	Fourteen channel samples yielded a mean value of 6.38 grams per tonne gold and 42.17 grams per tonne silver over a length of 59.5 metres.
1989	Channel			Property File - R.M. Barker [1989-01-01]: Summary Report on the Zumar Group
DRILLHOLE		Gold	5.0 g/t	
	Assay/analysis	Silver	31.5 g/t	Drill hole 86-1 over 0.9 metre.
1986	Drill Core			Assessment Report 16416
TRENCH		Silver	41.7 g/t	
	Assay/analysis			Grab samples from trenches.
1986	Grab			Assessment Report 16416
DRILLHOLE		Gold	3.5 g/t	
	Assay/analysis	Silver	31.5 g/t	Drill hole 82-2 over 1.70 metres.
1982	Drill Core			Assessment Report 16416
VEIN		Gold	4.7 g/t	
	Assay/analysis	Silver	42 g/t	Two lots of hand-cobbed vein material (totalling 55.1 tonnes) were shipped as a bulk sample, returning an averaging grade of 4.7 grams per tonne gold, 42 grams per tonne silver, 0.09 per cent copper, 0.10 per cent lead and 0.10 per cent zinc.
1980	Bulk Sample	Copper	0.09 %	Assessment Report 21600
		Lead	0.10 %	
		Zinc	0.10 %	