

|                                  |                    |                         |
|----------------------------------|--------------------|-------------------------|
| <b>MINFILE Number:</b> 082LSW111 | <b>Name:</b> ZUMAR | <b>Status:</b> Prospect |
|----------------------------------|--------------------|-------------------------|

| Ore Zone/<br>Year/Report On | Tonnage/<br>Category | Commodity | Grade     | Reference/<br>Comments   |
|-----------------------------|----------------------|-----------|-----------|--|
| VEIN                        |                      | Gold      | 4.22 g/t  |  |
|                             | Assay/analysis       | Silver    | 61.4 g/t  | Assessment Report 27711  |
| 2004                        | Rock                 | Copper    | 0.256 %   |  |
| VEIN                        |                      | Gold      | 12.30 g/t |  |
|                             | Assay/analysis       | Silver    | 180 g/t   | Two samples (3816 and 3815) yielded 12.30 and 11.40 grams per tonne gold with 180 and 109 grams per tonne silver over 0.35 and 0.42 metre, respectively.   |
| 2001                        | Chip                 |           |           | Assessment Report 26858  |
| VEIN                        |                      | Gold      | 6.38 g/t  |  |
|                             | Assay/analysis       | Silver    | 42.17 g/t | Fourteen channel samples yielded a mean value of 6.38 grams per tonne gold and 42.17 grams per tonne silver over a length of 59.5 metres.  |
| 1989                        | Channel              |           |           | Property File - R.M. Barker [1989-01-01]: Summary Report on the Zumar Group  |
| DRILLHOLE                   |                      | Gold      | 5.0 g/t   |  |
|                             | Assay/analysis       | Silver    | 31.5 g/t  | Drill hole 86-1 over 0.9 metre.  |
| 1986                        | Drill Core           |           |           | Assessment Report 16416  |
| TRENCH                      |                      | Silver    | 41.7 g/t  |  |
|                             | Assay/analysis       |           |           | Grab samples from trenches.  |
| 1986                        | Grab                 |           |           | Assessment Report 16416  |
| DRILLHOLE                   |                      | Gold      | 3.5 g/t   |  |
|                             | Assay/analysis       | Silver    | 31.5 g/t  | Drill hole 82-2 over 1.70 metres.  |
| 1982                        | Drill Core           |           |           | Assessment Report 16416  |
| VEIN                        |                      | Gold      | 4.7 g/t   |  |
|                             | Assay/analysis       | Silver    | 42 g/t    | Two lots of hand-cobbed vein material (totalling 55.1 tonnes) were shipped as a bulk sample, returning an averaging grade of 4.7 grams per tonne gold, 42 grams per tonne silver, 0.09 per cent copper, 0.10 per cent lead and 0.10 per cent zinc. |
| 1980                        | Bulk Sample          | Copper    | 0.09 %    | Assessment Report 21600  |
|                             |                      | Lead      | 0.10 %    |  |
|                             |                      | Zinc      | 0.10 %    |  |