MINFILE Number: 082M 125 **Name:** COMPLEX **Status:** Developed Prospect

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
B 2011 N	Assay/analysis Rock	Lead Zinc Silver	19.96 % 0.57 % 171 g/t	four samples (545640 through 545643) for the area of the Bass shaft yielded values from 4.48 to 19.96 per cent lead, 0.05 to 0.57 per cent zinc and 48 to 171 grams per tonne silver Williams, J.D. (2012-06-12): Technical Report on the Copper King – Cotton Belt Property
OUTCROP 1966	Assay/analysis Chip	Silver Lead Zinc	97.0000 g/t 5.3700 % 6.5100 %	Average of 21 surface chip samples across 1.4 metres along zone. Property File (Report by A.R. Allen, 1966).
B 1951 N	Assay/analysis Chip	Lead Zinc Silver	2.80 % 2.50 % 68.6 g/t	a sample taken south east of the Bass shaft over 76.2 centimetres Williams, J.D. (2012-06-12): Technical Report on the Copper King – Cotton Belt Property