

MINFILE Number:		Name:		Status:	
Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments	
DUMP 1976	N	Copper Assay/analysis Grab	5.0 % Copper Lead Zinc Silver	grab samples from the Copper King adit dump Williams, J.D. (2012-06-12): Technical Report on the Copper King – Cotton Belt Property	
DUMP 1976	N	Assay/analysis Grab	1.50 % 5.40 % 2.99 % 80.23 g/t	a sample from the McLeod adit dump Williams, J.D. (2012-06-12): Technical Report on the Copper King – Cotton Belt Property	
UNDERGROUND 1970	N	Assay/analysis Chip	Copper 3.55 %	underground sampling of the Copper King workings are reported to have yielded from 1.99 per cent copper over 2.9 metres true width near the portal to 3.55 per cent copper over 0.9 metre true width at approximately 33 metre along the adit Williams, J.D. (2012-06-12): Technical Report on the Copper King – Cotton Belt Property	
ADIT 1951	N	Assay/analysis Chip	Copper Silver Gold 1.00 % 37.7 g/t 0.17 g/t	a sample taken near the Copper King adit portal over 2.134 metres Williams, J.D. (2012-06-12): Technical Report on the Copper King – Cotton Belt Property	
MAC 1951	N	Assay/analysis Chip	Lead Zinc Silver 4.69 % 5.44 % 71.7 g/t	the average of four samples taken the surface exposure of the McLeod zone Williams, J.D. (2012-06-12): Technical Report on the Copper King – Cotton Belt Property	