

<b>MINFILE Number:</b> 082M 273	<b>Name:</b> GQ	<b>Status:</b> Showing
---------------------------------	-----------------	------------------------

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
D		Gold	7.15 g/t	float sample (GQ09-08) from the Spur D road
2009	N	Copper	0.111 %	Assessment Report 31172
	Assay/analysis	Tungsten	0.336 %	
	Grab	Bismuth	0.167 %	
D		Gold	8.5 g/t	float sample (GQ08-05) from the Spur D road
2008	N			Assessment Report 30489
	Assay/analysis			
	Grab			
D		Gold	11.57 g/t	float sample (GQ06-07) from the Spur D road
2006	N	Copper	0.11 %	Assessment Report 28805
	Assay/analysis			
	Grab			
NE		Gold	3.07 g/t	a rock sample (GQ06-19) from the NE zone
2006	N			Assessment Report 28805
	Assay/analysis			
	Rock			
SOUTHWEST		Gold	1.58 g/t	rock sample (WP 023R) from the SW zone
2000	N			Assessment Report 26423
	Assay/analysis			
	Rock			
NE		Gold	1.98 g/t	chip sampling (SCB 13+53R) of the NE zone yielded
2000	N	Tungsten	0.866 %	up to 1.98 grams per tonne gold across 0.6 metres,
	Assay/analysis			while other samples (WP104) yielded up to 0.866 per
	Chip			cent tungsten
				Assessment Report 26423
NE		Gold	1.2500 g/t	Grab sample by W. Gruenwald.
1999	N	Copper	0.0510 %	Fieldwork 1999, page 210.
	Assay/analysis	Tungsten	0.0250 %	
	Grab	Bismuth	0.0090 %	