MINFILE Number: 082N 004 **Name:** WOOLSEY **Status:** Past Producer

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
DUMP 1987 N	Assay/analysis Grab	Lead Zinc Tungsten Silver	1.51 % 1.33 % 0.03 % 46.6 g/t	four dump samples from the no. 8, 9 and 10 levels yielded from 0.08 to 1.51 per cent lead, trace to 1.33 per cent zinc, trace to 0.03 per cent tungsten and 5.5 to 46.6 grams per tonne silver Property File - Albar Resources Ltd. [1989-04-28]: Prospectus Report - Regal Silver Property
TOTAL 1982 Y	590,703 t Unclassified	Silver Copper Lead Tin Tungsten Zinc	71.6000 g/t 1.1000 % 2.6600 % 0.1300 % 0.0150 % 1.2600 %	Reported reserves. Prospectus, Gunsteel Resources Inc., April 29, 1986.
DRILLHOLE 1980 N	Assay/analysis Drill Core	Zinc Tungsten	18 % 0.52 %	diamond drilling yielded up to 18 per cent zinc over 0.3 metre and 0.52 per cent tungsten over 0.05 metre in hole RS-82-2, located to the north east on Clabon Creek Assessment Report 8963
MAIN 1971 N	658,616 t Unclassified	Silver Lead Zinc	90.3 g/t 2.55 % 1.15 %	This was revised in 1971, after further underground sampling, for reserve of 658,616 tonnes grading 90.3 grams per tonne silver, 2.55 per cent lead and 1.15 per cent zinc with an additional block of 16,964 tonnes grading 1.05 per cent tungsten trio-oxide Property File - Albar Resources Ltd. [1989-04-28]: Prospectus Report - Regal Silver Property
MAIN 1969 N	590,758 t Unclassified	Silver Lead Zinc Copper Tin Tungsten Cadmium	92.0 g/t 2.66 % 1.26 % 1.10 % 0.13 % 0.02 % 0.02 %	an estimate of proven and probable reserves of 590,758 tonnes grading 92.0 grams per tonne silver, 2.66 per cent lead, 1.26 per cent zinc, 1.10 per cent copper, 0.13 per cent tin, 0.02 per cent cadmium and 0.02 per cent tungsten tri-oxide was reported, including a block of 25,129 tonnes grading 1.31 per cent tungsten tri-oxide Property File - Albar Resources Ltd. [1989-04-28]: Prospectus Report - Regal Silver Property
NO. 4 1942 N	Assay/analysis Chip	Silver Lead Zinc Tin	78.7 g/t 0.20 % 2.28 % 0.35 %	underground sampling of the workings adjoining the no. 4 level of the Snowflake (MINFILE 082N 003) mine but on the Regal Silver property, yielded an average of 78.7 grams per tonne silver, 0.20 per cent lead, 2.28 per cent zinc and 0.35 per cent tin over a length of 31.8 metres and a width of 0.51 metre Property File - C.S. Lord [1942-12-01]: Assay Plan Map - Part of Snowflake Level

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
UNDERGROUND 1942 N	Assay/analysis Drill Core	Tin Lead Zinc	0.15 % 1.28 % 0.35 %	underground diamond drilling yielded: 0.62 per cent tin, 0.95 per cent lead and 0.41 per cent zinc over 48 centimetres in hole no. 1; 0.15 per cent tin, 1.28 per cent lead and 0.35 per cent zinc over 1.6 metres in hole no. 2 and 0.08 per cent tin, 0.86 per cent lead with 1.97 per cent zinc over 1.11 metres in hole no. 3; 0.36 per cent time over 12 centimetres in hole no. 4. Silver values were not reported. Property File - C.S. Lord [1943-02-26]: Diamond Drilling and Sampling at Regal Silver and Snowflake Properties
NO. 2 1930 N	Assay/analysis Chip	Silver Lead Zinc Tin	171.0 g/t 5.0 % 1.2 % 0.1 %	sampling of the no. 5 vein from the no. 2 tunnel yielded an average of 171.0 grams per tonne silver, 5.0 per cent lead, 1.2 per cent zinc with 0.1 per cent tin over a length of 105 metres and a width of 4.5 metres Property File - F.W. Guernsey [1930-11-30]: Report - Regal Silver Mines Limited - 19 Mineral Claims
NO. 3 1930 N	Assay/analysis Chip	Silver Lead Zinc Tungsten	102.6 g/t 1.5 % 0.9 % 0.5 %	Sampling of the no. 6 vein from the no. 3 level yielded an average of 102.6 grams per tonne silver, 1.5 per cent lead, 0.9 per cent zinc and 0.5 per cent tin over a length of 157.5 metres and a width of 2.4 metres, with individual samples yielding up to 2.9 per cent tin Property File - F.W. Guernsey [1930-11-30]: Report - Regal Silver Mines Limited - 19 Mineral Claims
NO. 3 1930 N	Assay/analysis Chip	Silver Lead Zinc Tin	229.1 g/t 6.1 % 1.8 % 0.5 %	sampling of the no. 5 vein from the no. 3 level averaged 229.1 grams per tonne silver, 6.1 per cent lead, 1.8 per cent zinc and 0.5 per cent tin over a length of 72 metres and a width of 1.95 metres Property File - F.W. Guernsey [1930-11-30]: Report - Regal Silver Mines Limited - 19 Mineral Claims