

MINFILE Inventory Detail Report BC Geological Survey Ministry of Energy, Mines and Petroleum Resources

but on the Regal Silver property, yielded an average of

78.7 grams per tonne silver, 0.20 per cent lead, 2.28 per cent zinc and 0.35 per cent tin over a length of 31.8

Property File - C.S. Lord [1942-12-01]: Assay Plan

metres and a width of 0.51 metre

Map - Part of Snowflake Level

MINFILE Number: 082N 004 Name: WOOLSEY **Status:** Past Producer Ore Zone/ Tonnage/ Commodity Grade Reference/ Year/Report On Category **Comments** 1.51 % DUMP Lead four dump samples from the no. 8, 9 and 10 levels Zinc 1.33 % yielded from 0.08 to 1.51 per cent lead, trace to 1.33 Assay/analysis Tungsten 0.03 % per cent zinc, trace to 0.03 per cent tungsten and 5.5 to Grab 1987 N Silver 46.6 g/t 46.6 grams per tonne silver Property File - Albar Resources Ltd. [1989-04-28]: Prospectus Report - Regal Silver Property TOTAL 71.6000 g/t 590,703 Silver Reported reserves. 1.1000 % Copper Prospectus, Gunsteel Resources Inc., April 29, 1986. Unclassified 2.6600 % Lead Y 1982 0.1300 % Tin Tungsten 0.0150 % Zinc 1.2600 % DRILLHOLE Zinc 18 % diamond drilling yielded up to 18 per cent zinc over 0.3 Tungsten 0.52 % metre and 0.52 per cent tungsten over 0.05 metre in hole Assay/analysis RS-82-2, located to the north east on Clabon Creek Drill Core 1980 Ν Assessment Report 8963 MAIN 658,616 Silver 90.3 g/t This was revised in 1971, after further underground Lead 2.55 % sampling, for reserve of 658,616 tonnes grading 90.3 Unclassified Zinc 1.15 % grams per tonne silver, 2.55 per cent lead and 1.15 per 1971 N cent zinc with an additional block of 16,964 tonnes grading 1.05 per cent tungsten trio-oxide Property File - Albar Resources Ltd. [1989-04-28]: Prospectus Report - Regal Silver Property MAIN 590,758 Silver 92.0 g/t an estimate of proven and probable reserves of 590,758 Lead 2.66 % tonnes grading 92.0 grams per tonne silver, 2.66 per Unclassified Zinc 1.26 % cent lead, 1.26 per cent zinc, 1.10 per cent copper, 0.13 1969 N 1.10 % Copper per cent tin, 0.02 per cent cadmium and 0.02 per cent Tin 0.13 % tungsten tri-oxide was reported, including a block of 0.02 % Tungsten 25,129 tonnes grading 1.31 per cent tungsten tri-oxide Cadmium 0.02 % Property File - Albar Resources Ltd. [1989-04-28]: Prospectus Report - Regal Silver Property NO. 4 Silver 78.7 g/t underground sampling of the workings adjoining the no. Lead 0.20 % 4 level of the Snowflake (MINFILE 082N 003) mine Assay/analysis

2.28 %

0.35 %

Zinc

Tin

Chip

N

1942

Ore Zone/ Year/Report On		Tonnage/ Category	Commodity	Grade	Reference/ Comments
UNDERGI	ROUND N	Assay/analysis Drill Core	Tin Lead Zinc	0.15 % 1.28 % 0.35 %	underground diamond drilling yielded: 0.62 per cent tin, 0.95 per cent lead and 0.41 per cent zinc over 48 centimetres in hole no. 1; 0.15 per cent tin, 1.28 per cent lead and 0.35 per cent zinc over 1.6 metres in hole no. 2 and 0.08 per cent tin, 0.86 per cent lead with 1.97 per cent zinc over 1.11 metres in hole no. 3; 0.36 per cent time over 12 centimetres in hole no. 4. Silver values were not reported. Property File - C.S. Lord [1943-02-26]: Diamond Drilling and Sampling at Regal Silver and Snowflake Properties
NO. 2 1930	N	Assay/analysis Chip	Silver Lead Zinc Tin	171.0 g/t 5.0 % 1.2 % 0.1 %	sampling of the no. 5 vein from the no. 2 tunnel yielded an average of 171.0 grams per tonne silver, 5.0 per cent lead, 1.2 per cent zinc with 0.1 per cent tin over a length of 105 metres and a width of 4.5 metres Property File - F.W. Guernsey [1930-11-30]: Report - Regal Silver Mines Limited - 19 Mineral Claims
NO. 3 1930	N	Assay/analysis Chip	Silver Lead Zinc Tungsten	102.6 g/t 1.5 % 0.9 % 0.5 %	Sampling of the no. 6 vein from the no. 3 level yielded an average of 102.6 grams per tonne silver, 1.5 per cent lead, 0.9 per cent zinc and 0.5 per cent tin over a length of 157.5 metres and a width of 2.4 metres, with individual samples yielding up to 2.9 per cent tin Property File - F.W. Guernsey [1930-11-30]: Report - Regal Silver Mines Limited - 19 Mineral Claims
NO. 3 1930	N	Assay/analysis Chip	Silver Lead Zinc Tin	229.1 g/t 6.1 % 1.8 % 0.5 %	sampling of the no. 5 vein from the no. 3 level averaged 229.1 grams per tonne silver, 6.1 per cent lead, 1.8 per cent zinc and 0.5 per cent tin over a length of 72 metres and a width of 1.95 metres Property File - F.W. Guernsey [1930-11-30]: Report - Regal Silver Mines Limited - 19 Mineral Claims

Monday, November 17, 2025 MINFILE Number: 082N 004 Page 2 of 2