**MINFILE Number:** 082N 027 **Name:** MOOSE CREEK **Status:** Developed Prospect

| Ore Zone/ Year/Report On | Tonnage/ Category | Commodity | Grade | Reference/ Comments |
|---|---|---|---|---|
| MAIN<br>1991 Y | 1,900 kt<br>Inferred | Magnetite | 5.5000 % | Magnetite contained in broken talus material. The average grade of ore is 5.5 per cent with a cutoff grade of 2.5 per cent.<br>Prospectus, St. Paul Minerals Ltd., February 12, 1991. |
| MAIN<br>1991 Y | 362 kt<br>Indicated | Magnetite | 5.5000 % | Magnetite contained in broken talus material. The average grade of ore is 5.5 per cent with a cutoff grade of 2.5 per cent.<br>Prospectus, St. Paul Minerals Ltd., February 12, 1991. |
| MAIN<br>1991 Y | 205 kt<br>Measured | Magnetite | 5.5000 % | Magnetite contained in broken talus material. The average grade of ore is 5.5 per cent with a cutoff grade of 2.5 per cent.<br>Prospectus, St. Paul Minerals Ltd., February 12, 1991. |