

MINFILE Number: 082N 086	Name: GRIZZLY	Status: Showing
---------------------------------	----------------------	------------------------

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
OUTCROP		Gold	2.34 g/t	An undescribed outcrop sample (151659), taken several hundred metres to the northwest and on strike of the historic adit yielded 2.34 grams per tonne gold, 76 grams per tonne silver and greater than 1.0 per cent copper Assessment Report 40486
2021	Assay/analysis Rock	Silver	76 g/t	
		Copper	1 %	
N				
TRENCH		Gold	0.99 g/t	a sub-crop sample (151637) from a pod of massive galena from the area of historic trenching Assessment Report 40486
2021	Assay/analysis Grab	Silver	2260 g/t	
		Lead	51.0 %	
N		Zinc	4.6 %	
ADIT		Gold	7.44 g/t	a float grab sample (148543) from a mineralized boulder located near the mouth of the adit Assessment Report 39435
2020	Assay/analysis Grab	Silver	6670 g/t	
		Lead	31.6 %	
N		Copper	5.72 %	
TRENCH		Gold	2.14 g/t	A grab sample (148580) of mineralized quartz vein from historic trenches yielded 2.14 grams per tonne gold, 1840 grams per tonne silver, 48.9 per cent lead and 10.2 per cent zinc Assessment Report 39435
2020	Assay/analysis Grab	Silver	1840 g/t	
		Lead	48.9 %	
N		Zinc	10.2 %	
DUMP		Gold	0.9500 g/t	Picked sample of vein material. Assessment Report 18053.
1988	Assay/analysis Grab	Copper	0.7100 %	
		Lead	0.5400 %	
N		Silver	315 g/t	
DRILLHOLE		Copper	16.90 %	Diamond drilling yielded intercepts of up to 16.90 per cent copper, 8.95 per cent lead, 6860 grams per tonne silver with 53.8 grams per tonne gold over 4.04 metres in hole A; 11.2 per cent copper, 14.8 per cent lead, 6240 grams per tonne silver with 27.9 grams per tonne gold over 4.75 metres in hole B; 6.14 per cent copper, 12.8 per cent lead, 3490 grams per tonne silver with 17.1 grams per tonne gold over 4.2 metres in hole D and 8.91 per cent copper, 9.12 per cent lead, 3560 grams per tonne silver with 22.3 grams per tonne gold over 3.05 metres in hole E Assessment Report 12482
1984	Assay/analysis Drill Core	Lead	8.95 %	
		Silver	6860 g/t	
N		Gold	53.8 g/t	
TRENCHES		Copper	1.04 %	Bulk sampling of historic trenches, totalling 267.7 kilograms, yielded an average of 1.04 per cent copper, 10.74 per cent lead, 0.046 per cent tungsten tri-oxide, 700 grams per tonne silver and 2.13 grams per tonne gold Assessment Report 11908
1983	Assay/analysis Bulk Sample	Lead	10.74 %	
		Silver	700 g/t	
		Gold	2.13 g/t	
N		Tungsten	0.046 %	

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
VEIN		Copper	1.89 %	A sample from a 40-centimetre-wide mineralized vein, located west of the adit portal, yielded 1.89 per cent copper, 647 grams per tonne silver and 4.44 grams per tonne gold over 0.3 metre Assessment Report 10954
	Assay/analysis	Silver	647 g/t	
1982	Rock	Gold	4.44 g/t	
TRENCH		Silver	269 g/t	A galena-bearing sample (3632) from a trench assayed 0.25 gram per tonne gold and 269 grams per tonne silver, while an undescribed (select?) sample (No.1) yielded 31.6 grams per tonne gold, 7170 grams per tonne silver, 19.4 per cent lead and 18.7 per cent copper Assessment Report 09745
1981	Assay/analysis Grab	Gold	0.25 g/t	