

|                                 |                   |                         |
|---------------------------------|-------------------|-------------------------|
| <b>MINFILE Number:</b> 092B 110 | <b>Name:</b> HOPE | <b>Status:</b> Prospect |
|---------------------------------|-------------------|-------------------------|

| Ore Zone/<br>Year/Report On | Tonnage/<br>Category                  | Commodity                                | Grade  | Reference/<br>Comments  |
|-----------------------------|---------------------------------------|--|--|---|
| ROADCUT<br><br>2022         | N<br><br>Assay/analysis<br>Rock       | Copper<br>Silver<br>Gold                 | 0.13 %<br>4.1 g/t<br>0.141 g/t                       | a rock sample (H619127) of quartz-carbonate-sulphide altered mafic volcanic rock hosting disseminated pyrite, chalcopyrite and sphalerite from the main (Road) occurrence area<br>Assessment Report 41178   |
| SAMPLE<br><br>2006          | N<br><br>Assay/analysis<br>Grab       | Zinc<br>Silver<br>Lead<br>Gold           | 0.15 %<br>0.10 g/t<br>0.015 %<br>0.40 g/t            | grab samples 926 to 928<br>Kelso, L. (2007-11-15): Independent Technical Report and Mineral Resource Estimation – Lara Polymetallic Property  |
| NORTHWEST<br><br>1986       | N<br><br>Assay/analysis<br>Drill Core | Copper                                   | 0.298 %  | Drill hole 86-R100 yielded intercepts of up to 0.298 per cent copper over 1.41 metres (true thickness, 153.66 to 156.07 metres down-hole)<br>Assessment Report 15737  |
| NORTHWEST<br><br>1986       | N<br><br>Assay/analysis<br>Drill Core | Copper                                   | 0.351 %  | hole 86-R102 yielded 0.351 per cent copper over 1.8 metres (137.90 to 139.70 metres down-hole)<br>Assessment Report 15737   |
| DRILLHOLE<br><br>1985       | N<br><br>Assay/analysis<br>Drill Core | Copper<br>Zinc                           | 0.32 %<br>0.74 %                                     | drill holes DDH-85-71, located approximately 200 to 300 metres northwest of the main (Road) occurrence area, yielded intercepts of up to 0.32 per cent copper with 0.74 per cent zinc over 0.86 metres (0.51 metre true thickness; 172.99 to 173.85 metres down-hole)<br>Assessment Report 14492                                    |
| DRILLHOLE<br><br>1985       | N<br><br>Assay/analysis<br>Drill Core | Zinc                                     | 0.42 %   | drill hole DDH-85-72, located approximately 200 to 300 metres northwest of the main (Road) occurrence area, yielded intercepts of up to 0.42 per cent zinc over 1.16 metres (0.53 metre true thickness; 143.46 to 144.62 metres down-hole),<br>Assessment Report 14492  |
| TRENCH<br><br>1982          | N<br><br>Assay/analysis<br>Rock       | Copper<br>Lead<br>Zinc<br>Silver<br>Gold | 3.46 %<br>0.62 %<br>10.83 %<br>305.4 g/t<br>0.17 g/t | a sample from a small lense of massive sulphides (sphalerite, pyrite and chalcopyrite) in a siliceous gangue, approximately 0.10 metre wide, hosted in pyritic felsic tuffs and/or chlorite schist exposed in the south end of trench 82-19, located approximately 200 metres northwest of the road zone<br>Assessment Report 11123 |
| TRENCH<br><br>1982          | N<br><br>Assay/analysis<br>Chip       | Gold                                     | 0.74 g/t   | Rock chip sampling of the rest of the trench yielded anomalous values of copper, lead, zinc, silver, and gold with gold averaging 0.74 gram per tonne over 23.4 metres<br>Assessment Report 11123   |

| Ore Zone/<br>Year/Report On  | Tonnage/<br>Category   | Commodity                                | Grade  | Reference/<br>Comments  |
|------------------------------|------------------------|--|--|---|
| ROADCUT<br><br>1981        N | Assay/analysis<br>Rock | Copper<br>Lead<br>Zinc<br>Silver<br>Gold | 0.21 %<br>0.85 %<br>1.77 %<br>25.0 g/t<br>2.94 g/t | three rock samples (81 BR-129 to 81 BR -131) from a road-cut exposure of mineralized baritic, felsic cherty tuff yielded from 0.20 to 0.21 per cent copper, 0.57 to 0.85 per cent lead, 0.70 to 1.77 per cent zinc, 1.84 to 2.12 per cent barium, 8.6 to 25.0 grams per tonne silver and 0.14 to 2.94 grams per tonne gold<br>Assessment Report 10116 |