

| | | |
|---------------------------------|--------------------------|------------------------|
| MINFILE Number: 092C 061 | Name: SILVER KING | Status: Showing |
|---------------------------------|--------------------------|------------------------|

| Ore Zone/ Year/Report On | Tonnage/ Category | Commodity | Grade | Reference/ Comments |
|-----------------------------|------------------------|--------------------------|----------------------------|---|
| COPPER QUEEN 2010 N | Assay/analysis Grab | Zinc Copper | 0.97 % 0.24 % | A select grab sample (8885) from the former Copper Queen crown grant assayed 0.97 per cent zinc, 0.24 per cent copper Assessment Report 31708 |
| SILVER 2010 N | Assay/analysis Grab | Copper Silver Zinc | 1.7 % 23.8 g/t 3.8 % | , two select outcrop grab samples, 8890 and 8891, from the former Silver King crown grant assayed 3.8 and 2.0 per cent zinc, 1.7 and 0.38 per cent copper with 23.8 grams per tonne and trace silver Assessment Report 31708 |
| SILVER 1986 N | Assay/analysis Rock | Gold | 6.856 g/t | six samples of the showing on the Silver King claim, the highest assay was 6.856 grams per tonne gold Assessment Report 15199 |
| COPPER QUEEN 1986 N | Assay/analysis Rock | Gold Silver | 12.34 g/t 20.9 g/t | A sample from a siliceous zone on the Copper Queen claim, 150 metres east of the Silver King, assayed 12.34 grams per tonne gold and 20.9 grams per tonne silver Assessment Report 15199 |