

<b>MINFILE Number:</b>	092C 144	<b>Name:</b>	SOGNIDORO	<b>Status:</b>	Prospect
------------------------	----------	--------------	-----------	----------------	----------

<b>Ore Zone/ Year/Report On</b>		<b>Tonnage/ Category</b>	<b>Commodity</b>	<b>Grade</b>	<b>Reference/ Comments</b>
SAMPLE  2011	N	Assay/analysis Grab	Copper	9.35 %	selected grab samples of hosting chalcopyrite and bornite from the quart-jasper-sulphide showings Assessment Report 32850
			Silver	28.9 g/t	
SAMPLE  1987	N	Assay/analysis Grab	Silver	0.5000 g/t	Sample of jasper (17827), cut by quartz veinlets containing pyrite, and disseminated and massive magnetite. Assessment Report 16802.
			Gold	0.7200 g/t	
			Copper	0.0418 %	
			Magnetite	41.6900 %	
VEIN  1987	N	Assay/analysis Grab	Silver	3.7000 g/t	Sample 17823 from Pit A containing quartz with iron oxides, malachite, chalcantite and up to 2 per cent chalcopyrite. Assessment Report 16802.
			Gold	0.5800 g/t	
			Copper	0.2800 %	