

MINFILE Number: 092E 002	Name: BEANO	Status: Past Producer
---------------------------------	--------------------	------------------------------

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
OPENCUT 1989 N	Assay/analysis Grab	Gold	53.1 g/t	average of nine samples from the No. 5 and 6 trenches Assessment Report 19677
OPENCUT 1989 N	Assay/analysis Chip	Gold	17.7 g/t	sampling of the No. 4 trench over 2.7 metres Assessment Report 19677
OUTCROP 1989 N	Assay/analysis Chip	Gold	47.3 g/t	over 7.5 metres, including 70.8 grams per tonne gold over 5.0 metres from a zone exposed along the creek canyon Assessment Report 19677
SAMPLE 1989 N	Assay/analysis Rock	Gold Copper	1.02 g/t 0.381 %	Sample BC-630, located approximately 300 metres down slope and to the south- southeast of the main trenched zone and from the southeastern (mapped) extent of the same limestone host unit as the main Beano zone. Assessment Report 19677
SAMPLE 1989 N	Assay/analysis Rock	Gold	3.3 g/t	Another rock sample (BC-757) taken from an area of andesitic volcanics exposed along a logging road approximately 1.1 kilometres to the south of the main Beano zone and at an elevation of approximately 340 meters Assessment Report 19677
DRILLHOLE 1983 N	Assay/analysis Drill Core	Gold	13.6 g/t	over 3.2 metres in hole DD3 Assessment Report 12573
DRILLHOLE 1983 N	Assay/analysis Drill Core	Gold	19.7 g/t	over 2.6 metres in hole DD4 Assessment Report 12573
DRILLHOLE 1983 N	Assay/analysis Drill Core	Gold	14.3 g/t	over 1.9 metres in hole DD5 Assessment Report 12573
DRILLHOLE 1983 N	Assay/analysis Drill Core	Gold	21.7 g/t	over 1.0 metre in hole DD6 Assessment Report 12573

Ore Zone/ Year/Report On		Tonnage/ Category	Commodity	Grade	Reference/ Comments
1981	N	Assay/analysis Chip	Gold Copper	83.4 g/t 0.23 %	a chip sample (ZEB-4) from the No. 4 cut, located at an elevation of 796 metres Assessment Report 9981
1981	N	Assay/analysis Grab	Gold Copper	67.7 g/t 0.11 %	A sample (ZEB-3) from a ore stockpile Assessment Report 9981
1972	N	Assay/analysis Chip	Gold	20.5 g/t	over 8.7 metres Property File - J.D. Mason [1973-09-10]: New Taku Mines Ltd. - 1972 Annual Report
1972	N	Assay/analysis Chip	Gold	48.6 g/t	over 0.6 metre of massive pyrrhotite (sample 1862) from the north adit Property File - New Taku Mines Ltd. [1972-08-22]: Sample Descriptions, Assays and Sketch Map - Beano
1972	N	Assay/analysis Chip	Gold	46.5 g/t	over 1.8 metres (sample 1863) from the north face of the south adit Property File - New Taku Mines Ltd. [1972-08-22]: Sample Descriptions, Assays and Sketch Map - Beano
1972	N	Assay/analysis Chip	Gold	148.8 g/t	sample 1854 over 1.8 metres from the No. 1 open cut Property File - New Taku Mines Ltd. [1972-08-22]: Sample Descriptions, Assays and Sketch Map - Beano
1946	N	Assay/analysis Grab	Gold	154.6 g/t	sampling of a 'lower' open cut over 2.7 metres Property File - E. Crowe (1941-07-15): Report on the Beano Group of Mining Claims; W.A. Lammers [1946-07-04]: Report - Beano Group
1941	N	Assay/analysis Channel	Gold	98.5 g/t	channel samples (No.3) over 3.38 metres from open cut No. 1 Property File - E. Crowe [1941-07-15]: Report on the Beano Group of Mining Claims
1939	N	Assay/analysis Grab	Gold	62.6 g/t	grab samples taken across 5.1 metres of an open cut Property File - H.G. Lynch [1939-04-27]: Letter Re: Preliminary Examination of the Beano property
1938	N	Assay/analysis Grab	Silver Gold	6.8000 g/t 321.7000 g/t	Massive pyrrhotite, Number 4 Cut. Minister of Mines Bulletin 27, page 138.