

<b>MINFILE Number:</b> 092E 018	<b>Name:</b> JUNE	<b>Status:</b> Prospect
---------------------------------	-------------------	-------------------------

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
VEIN  1986      N	Assay/analysis Chip	Gold Silver	38.6 g/t 406.8 g/t	In 1986, a 30 centimetre chip sample (4494) of mineralized quartz vein assayed 38.6 grams per tonne gold and 406.8 grams per tonne silver Assessment Report 14981
TUNNEL  1977      N	Assay/analysis Grab	Gold Silver Copper Lead Zinc	23.05 g/t 230.8 g/t 4.68 % 0.70 % 0.33 %	In 1977, sampling of the tunnel yielded values up to 23.05 grams per tonne gold, 230.8 grams per tonne silver, 4.68 per cent copper, 0.70 per cent lead and 0.33 per cent zinc over 36 centimetres (sample 16211) Assessment Report 6415
SHEAR  1946      N	Assay/analysis Channel	Silver Gold Copper	226.2400 g/t 24.6800 g/t 2.9000 %	Average of 9 samples over 0.49 metres. Property File (Sloan, W., 1946, page 3).