

MINFILE Number:	092E 074	Name:	EXTRA	Status:	Showing
------------------------	----------	--------------	-------	----------------	---------

Ore Zone/ Year/Report On		Tonnage/ Category	Commodity	Grade	Reference/ Comments
SAMPLE			Copper	0.338 %	A sample from a rusty shear zone, located in the general area of the Extra occurrence. Henneberry, R.T. (2018-02-05): 43-101 Technical Report – Tahsis Property
2015	N	Assay/analysis Grab			
SAMPLE			Gold	0.488 g/t	In 2006, a sample from a diorite plug enclosed in limestone, 300 metres to the southeast of the former adit, yielded 0.488 grams per tonne gold, 13.7 grams per tonne silver and greater than 10,000 parts per million copper. Assessment Report 28652
			Silver	13.7 g/t	
			Copper	1.0 %	
2006	N	Assay/analysis Rock			
OPENCUT			Gold	3.5700 g/t	Sample X90-D007, Langdon Resources Ltd. Prospectus, March 28, 1991.
			Silver	38.7000 g/t	
			Copper	14.1000 %	
1991	N	Assay/analysis Grab			
DRILLHOLE			Gold	0.075 g/t	Best values from different sections in hole one were 75 parts per billion gold, 0.2 parts per million silver and 580 parts per million copper. Assessment Report 20664
			Silver	0.2 g/t	
			Copper	0.058 %	
1990	N	Assay/analysis Drill Core			
FLOAT			Gold	10.8 g/t	Other mineralized rock and float samples taken in 1990 had ranges from trace gold, silver and copper to 10.8 grams per tonne gold, 20.0 grams per tonne silver and 7.97 per cent copper. Assessment Report 20664
			Silver	20 g/t	
			Copper	7.97 %	
1990	N	Assay/analysis Grab			