

<b>MINFILE Number:</b>	092E 074	<b>Name:</b>	EXTRA	<b>Status:</b>	Showing
------------------------	----------	--------------	-------	----------------	---------

<b>Ore Zone/ Year/Report On</b>		<b>Tonnage/ Category</b>	<b>Commodity</b>	<b>Grade</b>	<b>Reference/ Comments</b>
SAMPLE			Copper	0.338 %	A sample from a rusty shear zone, located in the general area of the Extra occurrence.
2015	N	Assay/analysis Grab			Henneberry, R.T. (2018-02-05): 43-101 Technical Report – Tahsis Property
SAMPLE			Gold	0.488 g/t	In 2006, a sample from a diorite plug enclosed in limestone, 300 metres to the southeast of the former adit, yielded 0.488 grams per tonne gold, 13.7 grams per tonne silver and greater than 10,000 parts per million copper. Assessment Report 28652
		Assay/analysis	Silver	13.7 g/t	
2006	N	Rock	Copper	1.0 %	
OPENCUT			Gold	3.5700 g/t	Sample X90-D007, Langdon Resources Ltd. Prospectus, March 28, 1991.
		Assay/analysis	Silver	38.7000 g/t	
1991	N	Grab	Copper	14.1000 %	
DRILLHOLE			Gold	0.075 g/t	Best values from different sections in hole one were 75 parts per billion gold, 0.2 parts per million silver and 580 parts per million copper. Assessment Report 20664
		Assay/analysis	Silver	0.2 g/t	
1990	N	Drill Core	Copper	0.058 %	
FLOAT			Gold	10.8 g/t	Other mineralized rock and float samples taken in 1990 had ranges from trace gold, silver and copper to 10.8 grams per tonne gold, 20.0 grams per tonne silver and 7.97 per cent copper. Assessment Report 20664
		Assay/analysis	Silver	20 g/t	
1990	N	Grab	Copper	7.97 %	