

<b>MINFILE Number:</b> 092F 031	<b>Name:</b> LEORA	<b>Status:</b> Past Producer
---------------------------------	--------------------	------------------------------

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
DUMP		Silver	10.2900 g/t	Sample R4699; zinc is greater than 2.0 per cent. Assessment Report 15956.
	Assay/analysis	Gold	6.3800 g/t	
1987	Grab	Cadmium	0.2000 %	
		Tungsten	0.0160 %	
		Zinc	2.0000 %	
DRILLHOLE		Gold	23.9 g/t	Drill holes 1 and 4, were completed beneath the former workings and returned intercepts of mineralized quartz vein yielding 23.9 grams per tonne gold over 0.24 metres and 4.5 grams per tonne gold over 0.43 metres, respectively. Assessment Report 15842
1985	Drill Core			
DUMP		Silver	10.29 g/t	Sample #R4699 from the Number Two level dump assayed 10.29 grams per tonne silver, 6.38 grams per tonne gold, 0.016 per cent tungsten, greater than 2.0 per cent zinc, and 0.2 per cent cadmium. Assessment Report 15956
	Assay/analysis	Gold	6.38 g/t	
1984	Grab	Tungsten	0.016 %	
		Zinc	2 %	
		Cadmium	0.2 %	
ADIT		Gold	11.0 g/t	In 1984, of the Number One level yielded values up to 11.0 grams per tonne gold over narrow widths. Assessment Report 15956
1984	Grab			
ADIT		Gold	132.5 g/t	In 1984, sampling of the Number Two level yielded values up to 132.50 grams per tonne gold and a 19 metre section averaged 5.14 grams per tonne gold on the number 2 adit. Assessment Report 15956, page 10
1984	Grab			
ADIT		Gold	300.13 g/t	In 1984, sampling of the vein yielded values up to 28.9 grams per tonne gold over erratic and narrow intervals on the Number 4 Level Adit. Assessment Report 15956
1984	Grab	Silver	2831 g/t	