

| | | |
|---------------------------------|-------------------|------------------------|
| MINFILE Number: 092F 058 | Name: O.K. | Status: Showing |
|---------------------------------|-------------------|------------------------|

| Ore Zone/ Year/Report On | Tonnage/ Category | Commodity | Grade | Reference/ Comments |
|-----------------------------|------------------------|----------------|---------------------------|--|
| SAMPLE 1982 N | Assay/analysis Chip | Silver Gold | 92.2300 g/t 6.1000 g/t | From a 37 centimetre chip sample. Assessment Report 11110. |
| SAMPLE 1939 N | Assay/analysis Grab | Silver Gold | 473.3 g/t 96.04 g/t | Previous sampling by B.C. Department of Mines (H. Sargent) in 1939, is reported to have yielded 96.04 grams per tonne gold and 473.3 grams per tonne silver across a 0.75 metre wide pyrite zone. Assessment Report 11110 |