

<b>MINFILE Number:</b> 092F 058	<b>Name:</b> O.K.	<b>Status:</b> Showing
---------------------------------	-------------------	------------------------

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
SAMPLE 1982      N	Assay/analysis Chip	Silver Gold	92.2300 g/t 6.1000 g/t	From a 37 centimetre chip sample. Assessment Report 11110.
SAMPLE 1939      N	Assay/analysis Grab	Silver Gold	473.3 g/t 96.04 g/t	Previous sampling by B.C. Department of Mines (H. Sargent) in 1939, is reported to have yielded 96.04 grams per tonne gold and 473.3 grams per tonne silver across a 0.75 metre wide pyrite zone. Assessment Report 11110