

MINFILE Number:	092F 076	Name:	IRON RIVER	Status:	Developed Prospect
------------------------	----------	--------------	------------	----------------	--------------------

Ore Zone/ Year/Report On		Tonnage/ Category	Commodity	Grade	Reference/ Comments
WEST			Iron	64.6 %	sampling of the West Skarn zone yielded from 11.2 to 64.6 per cent iron, 0.09 to 1.57 per cent copper and 0.3 to 14.2 grams per tonne silver from random chip samples Nicholson, G. (2008-12-10): 43-101 Technical Review Iron River Project
2007	N	Assay/analysis Grab	Copper	1.57 %	
			Silver	14.2 g/t	
WEST			Iron	35.8 %	a 2.0 metre long chip sample (MMR5) Nicholson, G. (2008-12-10): 43-101 Technical Review Iron River Project
2007	N	Assay/analysis Chip	Copper	0.94 %	
			Silver	4.5 g/t	
WEST			Copper	9.85 %	A grab sample from a pyrite lense with magnetite and chalcopyrite adjacent to a shear assayed 9.85 per cent copper, 750 grams per tonne silver and 47.8 per cent iron Assessment Report 13574
1985	N	Assay/analysis Grab	Silver	750 g/t	
			Iron	47.8 %	
EAST			Copper	0.26 %	In 1985, drill hole 86-IR-1 encountered a garnet-magnetite-chalcopyrite skarn from 72.00 to 117.45 metres depth, where it was terminated. The section assayed 0.26 per cent copper over 45.45 metres. Assessment Report 15877
1985	N	Assay/analysis Drill Core			
EAST			Gold	1.7 g/t	The final 10.26 metres of drill hole 86-IR-1 yielded 1.7 grams per tonne gold with maximum values of 4.1 grams per tonne gold over 2.03 metres and 4.5 grams per tonne gold over 1.5 metres at the beginning and end of the section, respectively Assessment Report 15877
1985	N	Assay/analysis Drill Core			
EAST			Copper	0.81 %	Drill hole 86-IR-3, located to the south west of 86-IR-1, intercepted the main copper zone from 100.21 to 151.79 metres depth yielding 0.81 per cent copper over 51.58 metres Assessment Report 15877
1985	N	Assay/analysis Drill Core			
EAST		1,450 kt	Copper	0.3490 %	Metallurgical testing has shown that a copper concentrate contains 1.4 - 1.7 grams per tonne gold and 2.4 - 3.4 grams per tonne silver. WWW http://www.info-mine.com/mining/properties/Wolf.html .
1974	Y	Indicated	Iron	26.4600 %	
WEST		3,175 kt	Copper	0.5170 %	Metallurgical testing has shown that a copper concentrate contains 1.4 - 1.7 grams per tonne gold, and 2.4 - 3.4 grams per tonne silver. WWW http://www.info-mine.com/mining/properties/Wolf.html .
1974	Y	Indicated	Iron	38.4800 %	