

<b>MINFILE Number:</b> 092F 129	<b>Name:</b> SUNSHINE (L.336)	<b>Status:</b> Developed Prospect
---------------------------------	-------------------------------	-----------------------------------

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
ADIT 2007 N	Assay/analysis Grab	Copper Silver	3.7 % 8.7 g/t	A select outcrop grab sample of weakly foliated copper skarn from a small, 2- by 1.5-metre adit. Assessment Report 29252
CREEK 2007 N	Assay/analysis Grab	Copper Silver	5.24 % 13.7 g/t	A select grab sample (362674) from a 1.0 metre thick skarn zone exposed in a creek bed yielded 5.24 per cent copper and 13.7 grams per tonne. Assessment Report 29574
SAMPLE 1988 N	Assay/analysis Chip	Silver Copper	10.5 g/t 0.12 %	Two chip samples (C4886 and C4888) from the Fern (L.332) assayed up to 10.5 grams per tonne silver, 0.12 per cent copper. Assessment Report 17714
SAMPLE 1988 N	Assay/analysis Chip	Silver Copper	13.5 g/t 1 %	One chip sample (D2759) from the Sunshine (L.336) assayed 13.5 grams per tonne silver and greater than 1 per cent copper. Assessment Report 17714