

MINFILE Number:	092F 152	Name:	GENERAL JAMES M. (L.318)	Status:	Showing
------------------------	----------	--------------	--------------------------	----------------	---------

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
SKARN 1991	Assay/analysis Grab	Copper Silver	1.83 % 14.8 g/t	In 1991, sampling of the skarn, as exposed by the second adit, assayed up to 1.83 per cent copper and 14.8 grams per tonne silver over 0.25 metres Assessment Report 21136
VEIN 1991	Assay/analysis Grab	Copper Silver	3.38 % 43.6 g/t	In 1991, a sample (4) from the vein, located east of the second adit, assayed 3.38 per cent copper and 43.6 grams per tonne silver 0.40 metres Assessment Report 21136
VEIN 1987	Assay/analysis Chip	Silver Copper Zinc	36.7000 g/t 4.3200 % 0.1500 %	1 metre chip sample across vein at the face of the main adit. Assessment Report 16354.
DUMP 1985	Assay/analysis Grab	Copper Silver	5.5 % 54.9 g/t	In 1985, two sample (2802 and 2803) of dump material from the adit assayed 5.5 and 2.7 per cent copper with 54.9 and 30.9 grams per tonne silver Assessment Report 14337