MINFILE Number: 092F 152 **Name:** GENERAL JAMES M. (L.318) **Status:** Showing

Ore Zone/ Year/Report On		Tonnage/ Category	Commodity	Grade	Reference/ Comments
SKARN			Copper	1.83 %	In 1991, sampling of the skarn, as exposed by the second adit, assayed up to 1.83 per cent copper and 14.8 grams per tonne silver over 0.25 metres Assessment Report 21136
			Silver	14.8 g/t	
		Assay/analysis			
1991	N	Grab			
VEIN			Copper	3.38 %	In 1991, a sample (4) from the vein, located east of the second adit, assayed 3.38 per cent copper and 43.6 grams per tonne silver 0.40 metres Assessment Report 21136
			Silver	43.6 g/t	
		Assay/analysis			
1991	N	Grab			
VEIN			Silver	36.7000 g/t	1 metre chip sample across vein at the face of the main adit. Assessment Report 16354.
			Copper	4.3200 %	
		Assay/analysis	Zinc	0.1500 %	
1987	N	Chip			
DUMP			Copper	5.5 %	In 1985, two sample (2802 and 2803) of dump material from the adit assayed 5.5 and 2.7 per cent copper with 54.9 and 30.9 grams per tonne silver Assessment Report 14337
			Silver	54.9 g/t	
		Assay/analysis			
1985	N	Grab			