

<b>MINFILE Number:</b> 092F 210	<b>Name:</b> J AND S	<b>Status:</b> Showing
---------------------------------	----------------------	------------------------

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
SAMPLE 1980      N	Assay/analysis Chip	Iron Copper	45.69 % 1.3 %	Chip samples assayed up to 1.3 per cent copper and 45.69 per cent iron Assessment Report 8898
SAMPLE 1965      N	Assay/analysis Chip	Copper Iron Titanium	0.1500 % 37.8000 % 0.1000 %	A 3 metre chip sample. Prospectus: Alberni Mines Ltd., 1965.