

MINFILE Number: 092F 223	Name: STROMBERG	Status: Showing
---------------------------------	------------------------	------------------------

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
SAMPLE 1944	N Assay/analysis Grab	Copper	2.3 %	a grab sample of sorted ore from the Bullion claim. Zinc values were also reported to be comparable with the copper values; however, no sphalerite was noted in the samples. Property File – Wilson, R. (1944-11-01) - Stromberg Group, Texada Island, Ridgeway R. Wilson and Associates
SAMPLE 1944	N Assay/analysis Grab	Copper	1.9 %	outcrop samples from the Delora claim yielded from 0.4 to 1.9 per cent copper. Zinc values were also reported to be comparable with the copper values; however, no sphalerite was noted in the samples. Property File – Wilson, R. (1944-11-01) - Stromberg Group, Texada Island, Ridgeway R. Wilson and Associates
SAMPLE 1926	N Assay/analysis Grab	Copper Zinc	1.0 % 1.5 %	average of two samples from the Kate claim Minister of Mines Annual Report 1926
SAMPLE 1926	N Assay/analysis Grab	Copper Zinc Silver	7.0 % 3.0 % 68.4 g/t	samples from the Delora claim yielded values of up to 7.0 per cent copper, 3.0 per cent zinc and 68.4 grams per tonne silver Minister of Mines Annual Report 1926
SHAFT 1925	N Assay/analysis Grab	Silver Copper	34.2800 g/t 8.7000 %	a grab sample of sorted ore from the historical Edith shaft Minister of Mines Annual Report 1925, page A288.
DUMP 1925	N Assay/analysis Grab	Copper	3.2 %	average of dump samples from the Bullion shaft Minister of Mines Annual Report 1925