

<b>MINFILE Number:</b> 092F 234	<b>Name:</b> BOLD	<b>Status:</b> Showing
---------------------------------	-------------------	------------------------

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
UPPER 1988	N Assay/analysis Channel	Copper Iron Gold	3.79 % 24.4 % 0.31 g/t	The upper Road Pit showing: Channel sample results include 0.31 gram per tonne gold, 3.79 per cent copper and 24.4 per cent iron over 1.6 metres Assessment Report 25265
UPPER 1988	N Assay/analysis Channel	Gold Copper Iron	0.45 g/t 4.36 % 30.7 %	The upper Road Pit showing: Channel sample results include 0.45 grams per tonne gold, 4.36 per cent copper and 30.7 per cent iron over 1.2 metres Assessment Report 25265
MIDDLE D 1988	N Assay/analysis Channel	Gold Copper Iron	0.75 g/t 1.446 % 10.9 %	The Middle Road Pit showing: Channel sample results include 0.75 gram per tonne gold, 1.446 per cent copper and 44.3 per cent iron over 10.90 metres Assessment Report 25265
SAMPLE 1988	N Assay/analysis Channel	Gold Copper Iron	1.72 g/t 3.96 % 33.2 %	An unnamed showing, located approximately 60 metres west of the Middle Road Pit showing: Channel sample results include 1.720 grams per tonne gold, 3.96 per cent copper and 33.2 per cent iron over 1.1 metres and 1.115 grams per tonne gold, 3.9 per cent copper and 56.8 per cent iron over 1.7 metres Assessment Report 25265
SKARN 1984	N Assay/analysis Grab	Silver Copper	8.9000 g/t 2.5000 %	A grab sample of a mineralized skarn zone from the Bold claims. Another skarn grab sample, 400 metres to the east-southeast assayed 0.29 per cent copper and 2.1 grams per tonne silver. Assessment Report 13003.