

## MINFILE Inventory Detail Report BC Geological Survey Ministry of Energy, Mines and Petroleum Resources

MINFILE Number: 092F 234 Name: BOLD Status: Showing

| MINFILE                     | umper: | U92F 234                  | 092F 234 Name: BOLD    |                               | Status: Snowing  |
|-----------------------------|--------|---------------------------|------------------------|-------------------------------|--|
| Ore Zone/<br>Year/Report On |        | Tonnage/<br>Category      | Commodity              | Grade                         | Reference/ Comments  |
| UPPER                       | N      | Assay/analysis<br>Channel | Copper<br>Iron<br>Gold | 3.79 %<br>24.4 %<br>0.31 g/t  | The upper Road Pit showing: Channel sample results include 0.31 gram per tonne gold, 3.79 per cent copper and 24.4 per cent iron over 1.6 metres   |
| UPPER                       |        |                           | Gold<br>Copper         | 0.45 g/t<br>4.36 %            | Assessment Report 25265  The upper Road Pit showing: Channel sample results  |
| 1988                        | N      | Assay/analysis<br>Channel | Iron                   | 30.7 %                        | include 0.45 grams per tonne gold, 4.36 per cent copper<br>and 30.7 per cent iron over 1.2 metres<br>Assessment Report 25265   |
| MIDDLE D                    | N      | Assay/analysis<br>Channel | Gold<br>Copper<br>Iron | 0.75 g/t<br>1.446 %<br>10.9 % | The Middle Road Pit showing: Channel sample results include 0.75 gram per tonne gold, 1.446 per cent copper and 44.3 per cent iron over 10.90 metres   |
| SAMPLE                      |        |                           | Gold<br>Copper         | 1.72 g/t<br>3.96 %            | Assessment Report 25265  An unnamed showing, located approximately 60 metres west of the Middle Road Pit showing: Channel sample   |
| 1988                        | N      | Assay/analysis<br>Channel | Iron                   | 33.2 %                        | results include 1.720 grams per tonne gold, 3.96 per cent copper and 33.2 per cent iron over 1.1 metres and 1.115 grams per tonne gold, 3.9 per cent copper and 56.8 per cent iron over 1.7 metres Assessment Report 25265 |
| SKARN<br>1984               | N      | Assay/analysis<br>Grab    | Silver<br>Copper       | 8.9000 g/t<br>2.5000 %        | A grab sample of a mineralized skarn zone from the Bold claims. Another skarn grab sample, 400 metres to the east-southeast assayed 0.29 per cent copper and 2.1 grams per tonne silver.  Assessment Report 13003.         |

Friday, May 9, 2025 MINFILE Number: 092F 234 Page 1 of 1