

<b>MINFILE Number:</b>	092F 234	<b>Name:</b>	BOLD	<b>Status:</b>	Showing
------------------------	----------	--------------	------	----------------	---------

Ore Zone/ Year/Report On		Tonnage/ Category	Commodity	Grade	Reference/ Comments
UPPER  1988	N	Assay/analysis Channel	Copper	3.79 %	The upper Road Pit showing: Channel sample results include 0.31 gram per tonne gold, 3.79 per cent copper and 24.4 per cent iron over 1.6 metres Assessment Report 25265
			Iron	24.4 %	
			Gold	0.31 g/t	
UPPER  1988	N	Assay/analysis Channel	Gold	0.45 g/t	The upper Road Pit showing: Channel sample results include 0.45 grams per tonne gold, 4.36 per cent copper and 30.7 per cent iron over 1.2 metres Assessment Report 25265
			Copper	4.36 %	
			Iron	30.7 %	
MIDDLE D  1988	N	Assay/analysis Channel	Gold	0.75 g/t	The Middle Road Pit showing: Channel sample results include 0.75 gram per tonne gold, 1.446 per cent copper and 44.3 per cent iron over 10.90 metres Assessment Report 25265
			Copper	1.446 %	
			Iron	10.9 %	
SAMPLE  1988	N	Assay/analysis Channel	Gold	1.72 g/t	An unnamed showing, located approximately 60 metres west of the Middle Road Pit showing: Channel sample results include 1.720 grams per tonne gold, 3.96 per cent copper and 33.2 per cent iron over 1.1 metres and 1.115 grams per tonne gold, 3.9 per cent copper and 56.8 per cent iron over 1.7 metres Assessment Report 25265
			Copper	3.96 %	
			Iron	33.2 %	
SKARN  1984	N	Assay/analysis Grab	Silver	8.9000 g/t	A grab sample of a mineralized skarn zone from the Bold claims. Another skarn grab sample, 400 metres to the east-southeast assayed 0.29 per cent copper and 2.1 grams per tonne silver. Assessment Report 13003.
			Copper	2.5000 %	