MINFILE Number: 092F 240 **Name:** FAITH LAKE **Status:** Prospect

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
DISCOVERY 1987 N	Assay/analysis Grab	Gold Silver	37.71 g/t 274.6 g/t	sampling of the Discovery vein assayed up to 37.71 grams per tonne gold and 274.6 grams per tonne silver over 20 centimetres (sample AD01351) Assessment Report 16866
VEIN 1987 N	Assay/analysis Grab	Gold Silver	3.84 g/t 139.3 g/t	sampling of the Galena vein yielded up to 3.84 grams per tonne gold and 139.3 grams per tonne silver over 0.2 metres (sample AD01446) Assessment Report 16866
SAMPLE 1987 N	Assay/analysis Grab	Gold Silver	167.45 g/t 72.3 g/t	Sampling of other veins, in the area, has yielded values up to 167.45 grams per tonne gold and 72.3 grams per tonne silver over 0.2 metres (sample AD01376) Assessment Report 16866
DRILLHOLE 1964 N	Assay/analysis Drill Core	Silver Gold Copper	120.0000 g/t 24.6900 g/t 3.0000 %	From a 15 centimetre drill interval. McDougall, J.J. (1964): Report on Faith Lake Gold-Copper 1963.