

MINFILE Inventory Detail Report BC Geological Survey Ministry of Energy, Mines and Petroleum Resources

BACON LAKE MINFILE Number: 092F 256 Status: Prospect Name:

					*
Ore Zone/ Year/Report On		Tonnage/ Category	Commodity	Grade	Reference/ Comments
1		Assay/analysis	Iron	35 %	In 2013, four diamond drill holes were completed yielding and average of 35.0 per cent iron over 8.0
2013	N	Drill Core			metres. Assessment Report 33963
2			Iron	30 %	In 2013, three diamond drill holes were completed
2013	N	Assay/analysis Drill Core			yielding an average of 30 per cent iron over 21 metres. Assessment Report 33963
SAMPLE			Gold	9.28 g/t	In 1997, a sample (RBL 2) assayed 9.28 grams per
		Assay/analysis	Iron	30 %	tonne gold and greater than 30 per cent iron over 2.0
1997	N	Grab			metres Assessment Report 25513
SAMPLE			Gold	21.5 g/t	a sample (B-87-001) of magnetite with erythrite, from a
		Assay/analysis	Iron Cobalt	20 % 1.06 %	1 by 2.5 metre exposure
1987	N	Grab	Cobait	1.00 /0	Assessment Report 16321
2			Iron	45 %	In 1951, five drill holes were completed on Pod 2
		Assay/analysis			showing magnetite intersections occurring from surface
1951	N	Drill Core			to a depth of 17.5 metres and ranging from 2 to 8 metres wide. Assays yielded an average 45 per cent iron over
					an average width of 5.7 metres Assessment Report 33963
1			Iron	45 %	In 1951, Pod 1 was drilled and channel sampled over a
		Assay/analysis			100 metres in length with magnetite intersections occurring from surface to 17.5 metres in depth. These
1951	N	Drill Core			ranged from 2 to 10.5 metre wide intercepts in seven
					drill holes with an average width of 4.8 metres yielding
					45 per cent iron Assessment Report 33963
					Assessment report 33703