

MINFILE Number: 092F 571	Name: CAMP LAKE	Status: Showing
---------------------------------	------------------------	------------------------

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
DRILLHOLE 2004	Assay/analysis Drill Core	Copper Gold Iron	0.057 % 0.015 g/t 4.74 %	In 2004, the best intercept obtained during the drilling was in the first hole (BCL-04-01), from 33.2 to 47.9 meters down-hole, which intersected 14.6 meters of 0.057 per cent copper, 0.015 grams per tonne gold and 4.74 per cent iron Assessment Report 27717
SAMPLE 2003	Assay/analysis Grab	Copper Molybdenum Gold Silver Iron	1.74 % 0.0076 % 0.477 g/t 6.8 g/t 32.2 %	In 2003, four selective grab samples yielded an average of 1.74 per cent copper, 0.0076 per cent molybdenum, 0.477 grams per tonne gold, 6.8 grams per tonne silver and 29.7 per cent iron with peak values of 3.977 per cent copper, 0.0244 per cent molybdenum, 0.706 grams per tonne gold, 11.4 grams per tonne silver and 32.2 per cent iron Assessment Report 27717
SAMPLE 1983	Assay/analysis Grab	Silver Gold	10.3 g/t 6.2 g/t	In 1983, a select grab sample (61918) assayed 10.3 grams per tonne silver and 6.2 grams per tonne gold Assessment Report 11921