

| | | |
|----------------------------------|------------------|-------------------------|
| MINFILE Number: 092GNE001 | Name: ROY | Status: Prospect |
|----------------------------------|------------------|-------------------------|

| Ore Zone/ Year/Report On | Tonnage/ Category | Commodity | Grade | Reference/ Comments |
|-----------------------------|-----------------------------------|--------------------------|--------------------------------|---|
| SAMPLE 1984 | N Assay/analysis Grab | Silver Copper Gold | 89.5 g/t 15.5 % 0.17 g/t | grab sample (13817) of massive sulphides Tom Heah [1984-12-01]: Geology and Geochemistry of the London Group Indian River, B. C. Rept. #144-016-84 |
| SAMPLE 1984 | N Assay/analysis Rock | Gold Silver Copper | 0.2 g/t 107 g/t 22.3 % | Sample RSC-C CDN Resource Laboratories Ltd. [1984-09-10]: Assay Reports - 1984 - Falconbridge Copper - Anaconda |
| TRENCH 1975 | N Assay/analysis Chip | Copper Silver Gold | 27.8 % 90.5 g/t 0.69 g/t | sample (IRA 34) from the main trench assayed 27.8 per cent copper, 90.5 grams per tonne silver and 0.69 grams per tonne gold over 1.2 metres Assessment Report 36023 |
| TUNNEL 1919 | N Assay/analysis Drill Core | Copper | 0.5 % | drilling from the Roy No.3 tunnel is reported to have intersected a pyritized granodiorite yielding 0.5 per cent copper towards the end of the hole Paul A. Lindberg [1975-09-29]: Geological Mapping and Economic Appraisal of the Indian River Section of the Britannia Claims |
| SAMPLE 1916 | N Assay/analysis Chip | Silver Copper | 54.8000 g/t 12.4000 % | Chip sample across 2.4 metres. Trace gold. Minister of Mines Annual Report 1916, page 368. |