

MINFILE Number:		Name:		Status:	
Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments	
ADIT 2006	N	Assay/analysis Chip	Gold Silver Copper Bismuth	0.52 g/t 931 g/t 48.7 % 0.521 %	a 0.5 metre chip sample (HC JL-02), taken from the adit portal vein Assessment Report 29487
DUMP 2005	N	Assay/analysis Grab	Copper Silver Gold	50.0 % 603 g/t 0.98 g/t	select sample (HC-05-01) of bornite vein material from the main adit dump Assessment Report 29487
DUMPS 1991	N	Assay/analysis Bulk Sample	Silver Gold Copper	80.0000 g/t 0.2700 g/t 1.0000 %	Composite sample PR90-11, a 13.61-kilogram bulk taken from the main adit and dumps area. The copper value is greater than 1 per cent. Assessment Report 22242.
ADIT 1983	N	Assay/analysis Grab	Silver Copper	194.7000 g/t 15.1600 %	Sample from main adit. Assessment Report 11619.
VEIN 1983	N	Assay/analysis Grab	Molybdenum	0.13 %	a sample of molybdenite bearing quartz vein near the adit Assessment Report 11619
ADIT 1965	N	Assay/analysis Rock	Silver Copper Molybdenum	99.5 g/t 8.26 % 0.10 %	seven samples, taken along 26.4 metres of the main vein in the adit, yielded an average of 99.5 grams per tonne silver, 8.26 per cent copper and 0.10 per cent molybdenum over a 0.84 metre width Assessment Report 752
SAMPLE 1965	N	Assay/analysis Grab	Copper Molybdenum	0.21 % 0.01 %	Sampling of the mineralized muscovite granite Assessment Report 752