

MINFILE Number: 092GNW005	Name: HOWE COPPER	Status: Prospect
----------------------------------	--------------------------	-------------------------

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
ADIT		Gold	0.52 g/t	a 0.5 metre chip sample (HC JL-02), taken from the adit portal vein Assessment Report 29487
	Assay/analysis	Silver	931 g/t	
2006	Chip	Copper	48.7 %	
		Bismuth	0.521 %	
DUMP		Copper	50.0 %	select sample (HC-05-01) of bornite vein material from the main adit dump Assessment Report 29487
	Assay/analysis	Silver	603 g/t	
2005	Grab	Gold	0.98 g/t	
DUMPS		Silver	80.0000 g/t	Composite sample PR90-11, a 13.61-kilogram bulk taken from the main adit and dumps area. The copper value is greater than 1 per cent. Assessment Report 22242.
	Assay/analysis	Gold	0.2700 g/t	
1991	Bulk Sample	Copper	1.0000 %	
ADIT		Silver	194.7000 g/t	Sample from main adit. Assessment Report 11619.
	Assay/analysis	Copper	15.1600 %	
1983	Grab			
VEIN		Molybdenum	0.13 %	a sample of molybdenite bearing quartz vein near the adit Assessment Report 11619
	Assay/analysis			
1983	Grab			
ADIT		Silver	99.5 g/t	seven samples, taken along 26.4 metres of the main vein in the adit, yielded an average of 99.5 grams per tonne silver, 8.26 per cent copper and 0.10 per cent molybdenum over a 0.84 metre width Assessment Report 752
	Assay/analysis	Copper	8.26 %	
1965	Rock	Molybdenum	0.10 %	
SAMPLE		Copper	0.21 %	Sampling of the mineralized muscovite granite Assessment Report 752
	Assay/analysis	Molybdenum	0.01 %	
1965	Grab			