

<b>MINFILE Number:</b> 092GNW008	<b>Name:</b> CHALICE	<b>Status:</b> Prospect
----------------------------------	----------------------	-------------------------

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
B 2012	N Assay/analysis Grab	Gold Silver	83.6 g/t 86.7 g/t	two samples (2012-012 and -018) from the C2 zone of the Beach area yielded 83.6 and 59.2 grams per tonne silver with 86.7 and 25.6 grams per tonne gold, respectively Assessment Report 33765
B 2012	N Assay/analysis Channel	Gold Silver	5 g/t 9 g/t	a channel sample (2012-14) from a separate zone of the Beach area assayed 5 grams per tonne gold and 9 grams per tonne silver 0.70 metre Assessment Report 33765
B 2009	N Assay/analysis Grab	Gold Silver	32.42 g/t 7 g/t	a grab sample (EG-09-14) from the hangingwall of a small dike hosting a narrow quartz vein on the Beach area yielded 32.42 grams per tonne gold and 7 grams per tonne silver Assessment Report 31010
B 1985	N Assay/analysis Drill Core	Gold	7.20 g/t	Drilling on the Beach zone yielded 7.20 grams per tonne gold over 0.6 metre in hole Beach B-2 Assessment Report 14736
C 1985	N Assay/analysis Drill Core	Gold Silver	13.1 g/t 25.0 g/t	drillhole DDH-2 on the C-2 zone yielded 13.1 grams per tonne gold and 25.0 grams per tonne silver over 0.3 metre Assessment Report 14736
CLIFF 1984	N Assay/analysis Chip	Gold	5.5 g/t	A chip sample (CF-18) over 2.0 metres of the cliff zone Assessment Report 12641
B 1982	N Assay/analysis Grab	Gold Silver	146.7 g/t 128.9 g/t	Re-sampling of historical pits and trenches along the shoreline yielded values of up to 146.7 grams per tonne gold and 128.9 grams per tonne silver (Sample R-CP-4) Assessment Report 11129
B 1970	N Assay/analysis Grab	Gold Silver	75.2 g/t 82.1 g/t	Two grab samples (13804F and 13805F) of quartz with massive pyrite from pits exposed near the shoreline assayed 75.2 and 68.7 grams per tonne gold with 82.1 and 54.7 grams per tonne silver, respectively Assessment Report 2722
NORTHEAST 1970	N Assay/analysis Grab	Gold Silver	137.5 g/t 85.8 g/t	three other grab samples (13806, 13807 and 1308F) from three other quartz-pyrite showings located approximately 150 to 230 metres to the northeast of the previous samples, yielded values from 48.6 to 137.5 grams per tonne gold with 44.5 to 85.8 grams per tonne silver Assessment Report 2722

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
PIT		Silver	14.0000 g/t	A 96-tonne bulk sample.
	Assay/analysis	Gold	11.0000 g/t	Assessment Report 11129, page 16.
1966	Bulk Sample	Copper	0.0800 %	